



Product Data

TITANLENE LDI300YY FOR INJECTION MOLDING

CHARACTER	LDI300YY is a low density polyethylene resin for injection molding and is a barefoot grade. LDI300YY meets the U.S. Food and Drug Administration (FDA) criteria for food contact use as specified in 21 CFR 177.1520 (c) 2.1 & (c) 2.2.
APPLICATIONS	Medium sized molding, Cosmetic containers, Bottle closures, Food containers.
ADVANTAGES	High stiffness, good toughness, excellent gloss.

<u>TYPICAL RESIN PROPERTIES</u>	<u>UNIT</u>	<u>LDI300YY</u> ^(a)	<u>ASTM METHOD</u> ^(b)
Melt index	g/10 min	20	D1238
Density	g/cm ³	0.920	D1505
Vicat softening point	°C	87	D1525

TYPICAL MECHANICAL PROPERTIES

Tensile strength at yield	kg/cm ²	120	D638
Tensile strength at break	kg/cm ²	100	D638
Elongation at break	%	120	D638
1% Secant modulus	kg/cm ²	1900	D638
Low temperature brittleness	°C	-35	D746

(a) Values shown are typical and are not to be considered as specifications.

(b) ASTM test methods are latest under the Society's current procedures.

Processing conditions

Melt temperature	: 160 - 240°C
Mold temperature	: 15 - 50°C

Shrinkage : 1.3 - 3.0% depending on the product wall thickness and molding parameters.

We cannot anticipate all conditions under which this information and our products, or the products of other manufacturers in combination with our products, may be used. We accept no responsibility for results obtained by the application of this information or the safety and suitability of our products, either alone or in combination with other products. Users are advised to make their own tests to determine the safety and suitability of each such product combination for their own purposes. Unless otherwise agreed in writing, we sell products without warranty, and buyers and users assume all responsibility and liability for loss or damage arising from the handling and use of our products, whether used alone or in combination with other products.

R01

LOTTE CHEMICAL TITAN (M) SDN. BHD. (Registration no. 198601005832 (154990-W))
 Plant Location : PLO 312, Jalan Tembaga 4, Pasir Gudang Industrial Estate, 81700 Pasir Gudang, Johor Bahru, Malaysia.
 T: +607. 253 8888 W: WWW.LOTTECHEM.MY

Titanex® • Titanlene® • Titanzex® • Titanpro® • Titanvene®