



Product Data

TITANPRO SM498

FOR INJECTION STRETCH BLOW MOLDING AND INJECTION MOLDING

CHARACTER	Polypropylene random copolymer. Titanpro SM498 is a clarified grade designed for high transparency articles which complies with the U.S. Food and Drug Administration (FDA) regulation as specified in 21 CFR 177.1520(a)(3)(i) and (c)3.1a. TSCA Registry: CAS# 9010-79-1
APPLICATIONS	High clarity oriented PP bottles for hot filled applications, moisture sensitive packaging, baby feeding bottles, toiletries and detergent packaging, thin walled containers, storage containers, large articles, housewares.
ADVANTAGES	Excellent clarity, good balance of rigidity and impact resistance, excellent moisture barrier, cycle time reduction with low processing melt temperature, utilities cost saving, suitable for hot filling and thin walled products.
FABRICATION	Equipment - injection stretch blow molding (ISBM) machine, injection molding machine. Techniques - standard processing.

TYPICAL RESIN PROPERTIES ^(a)	UNIT	SM498	ASTM METHOD ^(b)
Melt Flow Rate, at 230°C	g/10 min	20	D1238
Density	g/cm ³	0.9	D1505
Tensile Strength at Yield	kg/cm ²	300	D638
Elongation at Yield	%	10	D638
Flexural Modulus	kg/cm ²	13000	D790B
Notched Izod Impact Strength at 23°C	kg·cm/cm	6	D256A
Heat Deflection Temperature at 4.6 kg/cm ²	°C	85	D648
Rockwell Hardness	R scale	85	D785A
Water absorption after 24 hours	%	0.02	D570

(a) Values shown are average and are not to be considered as specifications.

(b) ASTM test methods are latest under the Society's current procedures.

Shrinkage : 1.3 - 1.4% depending on the product wall thickness and molding parameters.

UL Environment Claim Validation Mark

Titanpro® SM498 enables 10% of energy savings and 10% of reduced CO₂ emission on average for the production of clarified polypropylene injection molded articles.



10% Energy Savings



10% Reduced CO₂ Emission

We cannot anticipate all conditions under which this information and our products, or the products of other manufacturers in combination with our products, may be used. We accept no responsibility for results obtained by the application of this information or the safety and suitability of our products, either alone or in combination with other products. Users are advised to make their own tests to determine the safety and suitability of each such product combination for their own purposes. Unless otherwise agreed in writing, we sell products without warranty, and buyers and users assume all responsibility and liability for loss or damage arising from the handling and use of our products, whether used alone or in combination with other products.

R03

LOTTE CHEMICAL TITAN (M) SDN. BHD. (Registration no. 198601005832 (154990-W))

Plant Location : PLO 312, Jalan Tembaga 4, Pasir Gudang Industrial Estate, 81700 Pasir Gudang, Johor Bahru, Malaysia.
T: +607. 253 8888 W: WWW.LOTTECHEM.MY

Titanex® • Titanlene® • Titanzex® • Titanpro® • Titanvene®