

Technical Data Sheet

**Accutech HP0339M20CL**

Polypropylene Homopolymer
LyondellBasell Industries
Engineering Plastics

General

Material Status	• Commercial: Active
Availability	• North America
Filler / Reinforcement	• Mica, 20% Filler by Weight
Features	• Chemically Coupled
Forms	• Pellets

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density / Specific Gravity	1.03	1.02 g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	14 g/10 min	14 g/10 min	ASTM D1238
Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Modulus	363000 psi	2500 MPa	ASTM D638
Tensile Strength			ASTM D638
Yield	5080 psi	35.0 MPa	
Break	4500 psi	31.0 MPa	
Tensile Elongation			ASTM D638
Yield	5.0 %	5.0 %	
Break	12 %	12 %	
Flexural Modulus	435000 psi	3000 MPa	ASTM D790
Flexural Strength	7400 psi	51.0 MPa	ASTM D790
Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Notched Izod Impact	0.62 ft·lb/in	33 J/m	ASTM D256
Hardness	Nominal Value (English)	Nominal Value (SI)	Test Method
Rockwell Hardness (R-Scale)	80	80	ASTM D785
Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Deflection Temperature Under Load			ASTM D648
66 psi (0.45 MPa), Unannealed	259 °F	126 °C	
264 psi (1.8 MPa), Unannealed	160 °F	71.0 °C	

Additional Information

Ash Content, ASTM D2584: 20%

Notes

These are typical property values not to be construed as specification limits.

Processing Techniques

Specific recommendations for resin type and processing conditions can only be made when the end use, required properties and fabrication equipment are known.

Product Storage and Handling

- Product should be stored in dry conditions at temperatures below 50°C and protected from UV-light
- Improper storage may bring damage to the packaging and can negatively affects on the quality of this product
- Keep material completely dry for good processing

Company Information

For further information regarding the LyondellBasell company, please visit <http://www.lyb.com/>.

© LyondellBasell Industries Holdings, B.V. 2024

Disclaimer

Information in this document is accurate to the best of our knowledge at the date of publication. The document is designed to provide users general information for safe handling, use, processing, storage, transportation, disposal and release and does not constitute any warranty or quality specification,

Technical Data Sheet

**Accutech HP0339M20CL**

Polypropylene Homopolymer
LyondellBasell Industries
Engineering Plastics

either express or implied, including any warranty of merchantability or fitness for any particular purpose. Users shall determine whether the product is suitable for their use and can be used safely and legally.

In addition to any prohibitions of use specifically noted in this document, LyondellBasell may further prohibit or restrict the sale of its products into certain applications. For further information, please contact a LyondellBasell representative.

Trademarks

The Trademark referenced within the product name is owned or used by the LyondellBasell family of companies.