

Technical Data Sheet



Asi Polystyrene PS 3010-01

High Impact Polystyrene
LyondellBasell Industries
Distribution

Product Description

PS 3010-01 is a high impact grade of polystyrene characterized by good impact and processability. PS 3010 is widely used in the manufacture of housewares, toys, containers, appliance parts, speaker housings, and various types of extrusions.

General

Material Status	• Commercial: Active		
Availability	• North America		
Features	• Good Impact Resistance	• Good Processability	
Uses	• Appliance Components • Containers	• Household Goods • Housings	• Toys
Processing Method	• Extrusion	• Injection Molding	

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density / Specific Gravity	1.04	1.04 g/cm ³	
Melt Mass-Flow Rate (MFR) (200°C/5.0 kg)	3.0 g/10 min	3.0 g/10 min	ASTM D1238
Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Modulus	230000 psi	1590 MPa	ASTM D638
Tensile Strength (Break)	3900 psi	26.9 MPa	ASTM D638
Tensile Elongation (Break)	45 %	45 %	ASTM D638
Flexural Modulus	280000 psi	1930 MPa	ASTM D790
Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Notched Izod Impact	2.0 ft·lb/in	110 J/m	ASTM D256
Hardness	Nominal Value (English)	Nominal Value (SI)	Test Method
Rockwell Hardness (L-Scale)	47	47	ASTM D785
Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Deflection Temperature Under Load 264 psi (1.8 MPa), Annealed	178 °F	81.1 °C	ASTM D648
Vicat Softening Temperature	185 °F	85.0 °C	ASTM D1525

Notes

These are typical property values not to be construed as specification limits.

Processing Techniques

Specific recommendations for resin type and processing conditions can only be made when the end use, required properties and fabrication equipment are known.

Product Storage and Handling

- Product should be stored in dry conditions at temperatures below 50°C and protected from UV-light
- Improper storage may bring damage to the packaging and can negatively affects on the quality of this product
- Keep material completely dry for good processing

Company Information

For further information regarding the LyondellBasell company, please visit <http://www.lyb.com/>.

© LyondellBasell Industries Holdings, B.V. 2024

Disclaimer

Information in this document is accurate to the best of our knowledge at the date of publication. The document is designed to provide users general information for safe handling, use, processing, storage, transportation, disposal and release and does not constitute any warranty or quality specification, either express or implied, including any warranty of merchantability or fitness for any particular purpose. Users shall determine whether the product is suitable for their use and can be used safely and legally.

In addition to any prohibitions of use specifically noted in this document, LyondellBasell may further prohibit or restrict the sale of its products into certain applications. For further information, please contact a LyondellBasell representative.

Trademarks

Technical Data Sheet

**Asi Polystyrene PS 3010-01**

High Impact Polystyrene
LyondellBasell Industries
Distribution

The Trademark referenced within the product name is owned or used by the LyondellBasell family of companies.