

Technical Data Sheet



CirculenRecover EP PA66 GF50 H BLACK

Polyamide 66
LyondellBasell Industries
Engineering Plastics

Product Description

50% glass fiber reinforced, heat stabilized Polyamide 66 formulated on mechanical recycled sourcing. The product is available in black color, pellet form. Color match generally possible for dark colors only. Automotive structural applications are possible.

Sustainability:

According with the requirements of Standard ISO 14021:2016, Circulen Recover EP PA66 GF50 H BLACK contains 35% of recycled material that is fully based on pre-consumer waste.

Recycled content according to DIN SPEC 91446:2021-12: R35

Data Quality Level according to DIN SPEC 91446:2021-12: DQL4

Data Quality Level according to VDA 284: DQL Automotive

General

Material Status	• Commercial: Active
Availability	• Europe
Filler / Reinforcement	• Glass Fiber, 50% Filler by Weight
Recycled Content	• Post-Industrial (PIR)/Pre-Consumer, 45%
Features	• Heat Aging Resistant • Medium Viscosity
Processing Method	• Injection Molding
Resin ID (ISO 1043)	• PA66 GF50

Physical	Dry	Conditioned	Unit	Test Method
Density	1.57	--	g/cm ³	ISO 1183/A
Apparent (Bulk) Density	0.60 to 0.80	--	g/cm ³	ISO 60
Water Absorption (Saturation, 73°F (23°C))	--	1.2	%	ISO 62
Viscosity Number	140	--	cm ³ /g	ISO 307
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus	2.39E+6 (16500)	1.52E+6 (10500)	psi (MPa)	ISO 527-1/1A/1
Tensile Stress (Break)	31900 (220)	21800 (150)	psi (MPa)	ISO 527-2/1A/5
Tensile Strain (Break)	2.3	4.0	%	ISO 527-2/1A/5
Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength				ISO 179/1eA
-22°F (-30°C)	5.7 (12)	--	ft-lb/in ² (kJ/m ²)	
73°F (23°C)	6.7 (14)	9.5 (20)	ft-lb/in ² (kJ/m ²)	
Charpy Unnotched Impact Strength				ISO 179/1eU
-22°F (-30°C)	38 (80)	--	ft-lb/in ² (kJ/m ²)	
73°F (23°C)	40 ft-lb/in ² (85 kJ/m ²)	No Break	(kJ/m ²)	
Thermal	Dry	Conditioned	Unit	Test Method
Deflection Temperature Under Load				
66 psi (0.45 MPa), Unannealed	> 482 (> 250)	--	°F (°C)	ISO 75-2/Bf
264 psi (1.8 MPa), Unannealed	473 (245)	--	°F (°C)	ISO 75-2/Af

Technical Data Sheet

**CirculenRecover EP PA66 GF50 H BLACK**

Polyamide 66
LyondellBasell Industries
Engineering Plastics

Flammability	Dry	Conditioned	Unit	Test Method
Burning Rate	< 3.9 (< 100)	--	in/min (mm/min)	FMVSS 302
Flame Rating	HB	--		UL 94

Additional Information

- 1.) Not for use in food contact applications
- 2.) Not for use in medical or pharmaceutical applications

A Certificate of Analysis (CoA) is provided with every lot. DSC data is available on request. Content of not intentionally added other plastics is below 1%.

Technical Data Sheet



CirculenRecover EP PA66 GF50 H BLACK

Polyamide 66
LyondellBasell Industries
Engineering Plastics



Injection	Dry (English)	Dry (SI)
Drying Temperature	176 °F	80 °C
Drying Time	3.0 to 4.0 hr	3.0 to 4.0 hr
Suggested Max Moisture	0.04 to 0.10 %	0.04 to 0.10 %
Processing (Melt) Temp	536 to 572 °F	280 to 300 °C
Mold Temperature	140 to 248 °F	60 to 120 °C

Notes

These are typical property values not to be construed as specification limits.

Processing Techniques

Specific recommendations for resin type and processing conditions can only be made when the end use, required properties and fabrication equipment are known.

Product Storage and Handling

- Product should be stored in dry conditions at temperatures below 50°C and protected from UV-light
- Improper storage may bring damage to the packaging and can negatively affects on the quality of this product
- Keep material completely dry for good processing

Company Information

For further information regarding the LyondellBasell company, please visit <http://www.lyb.com/>.

© LyondellBasell Industries Holdings, B.V. 2024

Disclaimer

Information in this document is accurate to the best of our knowledge at the date of publication. The document is designed to provide users general information for safe handling, use, processing, storage, transportation, disposal and release and does not constitute any warranty or quality specification, either express or implied, including any warranty of merchantability or fitness for any particular purpose. Users shall determine whether the product is suitable for their use and can be used safely and legally.

In addition to any prohibitions of use specifically noted in this document, LyondellBasell may further prohibit or restrict the sale of its products into certain applications. For further information, please contact a LyondellBasell representative.

Trademarks

The Trademark referenced within the product name is owned or used by the LyondellBasell family of companies.