



Home / Products & Technology / Polymers / **Dexflex 727-UV BTFA ADOBE**

Dexflex 727-UV BTFA ADOBE

Description

Dexflex 727-UV BTFA ADOBE very high melt flow, medium flexural modulus, UV-stabilized, mineral-filled, thermoplastic elastomeric olefin has an excellent balance of properties and processability.

Availability

North America

[» CustomerXpress](#)[» Find a Sales Contact](#)[» Request Product Information](#)

Legend

SDS - Safety Data Sheet

PSB - Product Stewardship Bulletin

[Information](#)[SDS](#)[Safety Summary](#)

Product Data and Technical Information

Typical Properties

Melt Flow Rate (230°C/2.16 kg)	19 g/10 min
Density (23°C)	0.90 g/cm³
Flexural Modulus (1.3 mm/min, 1% Secant, Procedure A)	850 MPa
Mold Shrinkage	

Process

Injection Molding

Resin

Polypropylene Compounds

Prohibited Applications of Compounded Polyolefins:

The use of LyondellBasell Compounded Polyolefins in the following applications is prohibited:

- All parts for Aeronautical use
- All parts for Train transportation use
- Air bag unit housings
- Seat belt systems and mechanisms
- Brake systems and mechanisms
- Pedals (brake, gas, clutch)
- Steering systems and mechanisms

- All parts with flammability requirements for Building and Constructions
- All parts with flammability requirements for Industrial applications use
- All parts for Medical applications use

This site uses cookies. By continuing to browse the site, you agree to our use of cookies.

» **ACCEPT**

[Privacy](#)

