

[Home](#) / [Products & Technology](#) / [Polymers](#) / **Dexflex 727-UV YGYA**

Dexflex 727-UV YGYA

Description

Dexflex 727-UV YGYA very high melt flow, medium flexural modulus, UV-stabilized, mineral-filled, thermoplastic elastomeric olefin has an excellent balance of properties and processability.

Availability

North America

[» CustomerXpress](#)[» Find a Sales Contact](#)[» Request Product Information](#)

Legend

SDS - Safety Data Sheet

PSB - Product Stewardship Bulletin

[Information](#)[SDS](#)[PSB](#)[Safety Summary](#)

Product Data and Technical Information

Typical Properties

Melt Flow Rate (230°C/2.16 kg) **19 g/10 min**

Density (23°C) **0.90 g/cm³**

Flexural Modulus (1.3 mm/min, 1% Secant, Procedure A) **850 MPa**

Mold Shrinkage

Process

Injection Molding

Resin

Polypropylene Compounds

Applications

Automotive Parts, Exterior Automotive Applications

Prohibited Applications of Compounded Polyolefins:

The use of LyondellBasell Compounded Polyolefins in the following applications is prohibited:

- All parts for Aeronautical use

- All parts for Train transportation use
- Air bag unit housings
- Seat belt systems and mechanisms
- Brake systems and mechanisms
- Pedals (brake, gas, clutch)
- Steering systems and mechanisms
- All parts with flammability requirements for Building and Constructions
- All parts with flammability requirements for Industrial applications use
- All parts for Medical applications use

This site uses cookies. By continuing to browse the site, you agree to our use of cookies.

» ACCEPT

[Privacy](#)