



Home / Products & Technology / Polymers / **Dexflex D60-UV 4LLA**

Dexflex D60-UV 4LLA

Description

Dexflex D60-UV 4LLA is a thermoplastic olefinic elastomer (TPO) typically used for automotive exterior applications that require toughness, low thermal expansion and exceptional weatherability.

Availability

North America

[» CustomerXpress](#)[» Find a Sales Contact](#)[» Request Product Information](#)

Legend

SDS - Safety Data Sheet

PSB - Product Stewardship Bulletin

[Information](#)[SDS](#)[Safety Summary](#)

Product Data and Technical Information

Typical Properties

Melt Flow Rate (230°C/2.16 kg)	13 g/10 min
Density (23°C)	0.94 g/cm³
Flexural Modulus	150,000 psi
Mold Shrinkage	

Process

Injection Molding

Resin

Polypropylene Compounds

Applications

Automotive Parts, Exterior Automotive Applications

Prohibited Applications of Compounded Polyolefins:

The use of LyondellBasell Compounded Polyolefins in the following applications is prohibited:

- All parts for Aeronautical use

- All parts for Train transportation use
- Air bag unit housings
- Seat belt systems and mechanisms
- Brake systems and mechanisms
- Pedals (brake, gas, clutch)
- Steering systems and mechanisms
- All parts with flammability requirements for Building and Constructions
- All parts with flammability requirements for Industrial applications use
- All parts for Medical applications use

This site uses cookies. By continuing to browse the site, you agree to our use of cookies.

» ACCEPT

[Privacy](#)