

Technical Data Sheet



Diamond Asa S150UV

Acrylonitrile Styrene Acrylate
LyondellBasell Industries
Engineering Plastics

General

Material Status	• Commercial: Active
Availability	• North America
Features	• Good Weather Resistance • High Impact Resistance
Forms	• Pellets
Processing Method	• Injection Molding

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density / Specific Gravity			
--	1.06	1.06 g/cm ³	ASTM D792
73°F (23°C)	1.06 g/cm ³	1.06 g/cm ³	ISO 1183/A
Melt Mass-Flow Rate (MFR)			ASTM D1238 ISO 1133
220°C/10.0 kg	15 g/10 min	15 g/10 min	
230°C/3.8 kg	3.9 g/10 min	3.9 g/10 min	
Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Strength - Flow			
Yield, 73°F (23°C), Injection Molded ¹	6240 psi	43.0 MPa	ASTM D638
Yield, 73°F (23°C), Injection Molded	6350 psi	43.8 MPa	ISO 527-2
Flexural Modulus - Chord, Flow			
73°F (23°C), Injection Molded	316000 psi	2180 MPa	ASTM D790
73°F (23°C), Injection Molded	315000 psi	2170 MPa	ISO 178
Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Charpy Notched Impact Strength			ISO 179
-22°F (-30°C), Injection Molded	3.9 ft·lb/in ²	8.2 kJ/m ²	
73°F (23°C), Injection Molded	8.4 ft·lb/in ²	18 kJ/m ²	
Notched Izod Impact			
Flow : -22°F (-30°C), Injection Molded	2.0 ft·lb/in	110 J/m	ASTM D256
Flow : 73°F (23°C), Injection Molded	4.8 ft·lb/in	260 J/m	ASTM D256
-22°F (-30°C), Injection Molded	3.7 ft·lb/in ²	7.8 kJ/m ²	ISO 180
73°F (23°C), Injection Molded	9.8 ft·lb/in ²	21 kJ/m ²	ISO 180
Hardness	Nominal Value (English)	Nominal Value (SI)	Test Method
Rockwell Hardness			ASTM D785
R-Scale, 73°F (23°C), Injection Molded	100	100	
Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Deflection Temperature Under Load			
66 psi (0.45 MPa), Unannealed, Injection Molded	193 °F	89.2 °C	ASTM D648
66 psi (0.45 MPa), Unannealed	193 °F	89.3 °C	ISO 75-2/B
264 psi (1.8 MPa), Unannealed, 0.125 in (3.18 mm), Injection Molded	170 °F	76.7 °C	ASTM D648
264 psi (1.8 MPa), Unannealed, 0.250 in (6.35 mm)	181 °F	82.8 °C	ASTM D648
264 psi (1.8 MPa), Unannealed	170 °F	76.6 °C	ISO 75-2/A
Vicat Softening Temperature			
--	216 °F	102 °C	ASTM D1525 ²
--	215 °F	102 °C	ISO 306
CLTE			ISO 11359-2
Flow : -22 to 176°F (-30 to 80°C)	5.2E-5 in/in/°F	9.3E-5 cm/cm/°C	
Transverse : -22 to 176°F (-30 to 80°C)	5.4E-5 in/in/°F	9.8E-5 cm/cm/°C	

Technical Data Sheet



Diamond Asa S150UV

Acrylonitrile Styrene Acrylate
LyondellBasell Industries
Engineering Plastics



Injection	Nominal Value (English)	Nominal Value (SI)
Drying Temperature	176 to 185 °F	80 to 85 °C
Drying Time	2.0 to 4.0 hr	2.0 to 4.0 hr
Suggested Max Moisture	0.10 %	0.10 %
Suggested Shot Size	40 to 70 %	40 to 70 %
Rear Temperature	446 to 500 °F	230 to 260 °C
Middle Temperature	450 to 509 °F	232 to 265 °C
Front Temperature	455 to 522 °F	235 to 272 °C
Nozzle Temperature	428 to 522 °F	220 to 272 °C
Processing (Melt) Temp	428 to 522 °F	220 to 272 °C
Mold Temperature	104 to 176 °F	40 to 80 °C
Injection Rate	Fast	Fast
Back Pressure	75.0 to 150 psi	0.517 to 1.03 MPa

Technical Data Sheet



Diamond Asa S150UV

Acrylonitrile Styrene Acrylate
LyondellBasell Industries
Engineering Plastics

Notes

¹ 2.0 in/min (50 mm/min)

² Loading 1 (10 N)

Notes

These are typical property values not to be construed as specification limits.

Processing Techniques

Specific recommendations for resin type and processing conditions can only be made when the end use, required properties and fabrication equipment are known.

Product Storage and Handling

- Product should be stored in dry conditions at temperatures below 50°C and protected from UV-light
- Improper storage may bring damage to the packaging and can negatively affects on the quality of this product
- Keep material completely dry for good processing

Company Information

For further information regarding the LyondellBasell company, please visit <http://www.lyb.com/>.

© LyondellBasell Industries Holdings, B.V. 2024

Disclaimer

Information in this document is accurate to the best of our knowledge at the date of publication. The document is designed to provide users general information for safe handling, use, processing, storage, transportation, disposal and release and does not constitute any warranty or quality specification, either express or implied, including any warranty of merchantability or fitness for any particular purpose. Users shall determine whether the product is suitable for their use and can be used safely and legally.

In addition to any prohibitions of use specifically noted in this document, LyondellBasell may further prohibit or restrict the sale of its products into certain applications. For further information, please contact a LyondellBasell representative.

Trademarks

The Trademark referenced within the product name is owned or used by the LyondellBasell family of companies.