

Technical Data Sheet

**Diamond Pc 2006I.9001 White**

Polycarbonate
LyondellBasell Industries
Engineering Plastics

General

Material Status	• Commercial: Active
Availability	• North America
Additive	• Impact Modifier
Features	• Impact Modified
Forms	• Pellets


Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density / Specific Gravity ¹	1.20	1.20 g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) ² (300°C/1.2 kg)	9.0 g/10 min	9.0 g/10 min	ASTM D1238
Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Strength ³ (Break)	7830 psi	54.0 MPa	ASTM D638
Tensile Elongation ³ (Break)	88 %	88 %	ASTM D638
Flexural Modulus - Chord ⁴ (0.125 in (3.18 mm))	359000 psi	2480 MPa	ASTM D790
Flexural Strength ⁵ 0.125 in (3.18 mm), 1.97 in (50.0 mm) Span	14100 psi	97.0 MPa	ASTM D790
Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Charpy Notched Impact Strength	27 ft·lb/in ²	57 kJ/m ²	ISO 179
Notched Izod Impact -40°F (-40°C), 0.125 in (3.18 mm)	11 ft·lb/in	560 J/m	ASTM D256A
Unnotched Izod Impact (Area)	13.5 ft·lb/in ²	28.4 kJ/m ²	ASTM D256
Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Deflection Temperature Under Load 66 psi (0.45 MPa), Unannealed, 0.125 in (3.18 mm)	271 °F	133 °C	ASTM D648
264 psi (1.8 MPa), Unannealed, 0.125 in (3.18 mm)	243 °F	117 °C	

Technical Data Sheet



Diamond Pc 2006I.9001 White

Polycarbonate
LyondellBasell Industries
Engineering Plastics



Injection	Nominal Value (English)	Nominal Value (SI)
Drying Temperature	250 °F	121 °C
Drying Time	3.0 to 4.0 hr	3.0 to 4.0 hr
Suggested Max Moisture	0.02 %	0.02 %
Rear Temperature	500 to 590 °F	260 to 310 °C
Middle Temperature	500 to 590 °F	260 to 310 °C
Front Temperature	500 to 590 °F	260 to 310 °C
Nozzle Temperature	500 to 590 °F	260 to 310 °C
Processing (Melt) Temp	535 to 590 °F	279 to 310 °C
Injection Rate	Moderate	Moderate
Back Pressure	50.0 to 100 psi	0.345 to 0.689 MPa
Screw Speed	40 to 50 rpm	40 to 50 rpm

Injection Notes

Barrel Temps progressive increase from Rear to Front

Technical Data Sheet

**Diamond Pc 2006I.9001 White**

Polycarbonate
LyondellBasell Industries
Engineering Plastics

Notes

¹ Method A

² Procedure A

³ 0.20 in/min (5.0 mm/min)

⁴ 0.051 in/min (1.3 mm/min)

⁵ 0.50 in/min (13 mm/min)

Notes

These are typical property values not to be construed as specification limits.

Processing Techniques

Specific recommendations for resin type and processing conditions can only be made when the end use, required properties and fabrication equipment are known.

Product Storage and Handling

- Product should be stored in dry conditions at temperatures below 50°C and protected from UV-light
- Improper storage may bring damage to the packaging and can negatively affects on the quality of this product
- Keep material completely dry for good processing

Company Information

For further information regarding the LyondellBasell company, please visit <http://www.lyb.com/>.

© LyondellBasell Industries Holdings, B.V. 2024

Disclaimer

Information in this document is accurate to the best of our knowledge at the date of publication. The document is designed to provide users general information for safe handling, use, processing, storage, transportation, disposal and release and does not constitute any warranty or quality specification, either express or implied, including any warranty of merchantability or fitness for any particular purpose. Users shall determine whether the product is suitable for their use and can be used safely and legally.

In addition to any prohibitions of use specifically noted in this document, LyondellBasell may further prohibit or restrict the sale of its products into certain applications. For further information, please contact a LyondellBasell representative.

Trademarks

The Trademark referenced within the product name is owned or used by the LyondellBasell family of companies.