

## Technical Data Sheet

**Ferrex GPP20CN30AL**

Polypropylene  
LyondellBasell Industries  
Engineering Plastics

| General                                   |                                           |                        |             |
|-------------------------------------------|-------------------------------------------|------------------------|-------------|
| Material Status                           | • Commercial: Active                      |                        |             |
| Availability                              | • Latin America                           | • North America        |             |
| Filler / Reinforcement                    | • Calcium Carbonate, 21% Filler by Weight |                        |             |
| Features                                  | • Good Impact Resistance                  | • High Gloss           |             |
| Uses                                      | • Automotive Exterior Parts               | • Protective Coverings |             |
| Appearance                                | • Aluminum                                |                        |             |
| Forms                                     | • Pellets                                 |                        |             |
| Processing Method                         | • Injection Molding                       |                        |             |
| Physical                                  | Nominal Value (English)                   | Nominal Value (SI)     | Test Method |
| Density / Specific Gravity                | 1.06                                      | 1.06 g/cm <sup>3</sup> | ASTM D792   |
| Melt Mass-Flow Rate (MFR) (230°C/2.16 kg) | 23 g/10 min                               | 23 g/10 min            | ASTM D1238  |
| Mechanical                                | Nominal Value (English)                   | Nominal Value (SI)     | Test Method |
| Tensile Strength (Yield)                  | 2700 psi                                  | 18.6 MPa               | ASTM D638   |
| Tensile Elongation (Break)                | 150 %                                     | 150 %                  | ASTM D638   |
| Flexural Modulus                          | 170000 psi                                | 1170 MPa               | ASTM D790   |
| Flexural Strength (Yield)                 | 4100 psi                                  | 28.3 MPa               | ASTM D790   |
| Impact                                    | Nominal Value (English)                   | Nominal Value (SI)     | Test Method |
| Unnotched Izod Impact (73°F (23°C))       | No Break                                  | No Break               | ASTM D4812  |
| Gardner Impact                            | 250 in·lb                                 | 28.2 J                 | ASTM D3029  |
| Hardness                                  | Nominal Value (English)                   | Nominal Value (SI)     | Test Method |
| Durometer Hardness (Shore D)              | 65                                        | 65                     | ASTM D2240  |
| Thermal                                   | Nominal Value (English)                   | Nominal Value (SI)     | Test Method |
| Deflection Temperature Under Load         |                                           |                        | ASTM D648   |
| 66 psi (0.45 MPa), Unannealed             | 186 °F                                    | 85.6 °C                |             |
| 264 psi (1.8 MPa), Unannealed             | 130 °F                                    | 54.4 °C                |             |

## Technical Data Sheet



# Ferrex GPP20CN30AL

Polypropylene  
LyondellBasell Industries  
Engineering Plastics



| Injection               | Nominal Value (English)         | Nominal Value (SI)            |
|-------------------------|---------------------------------|-------------------------------|
| Drying Temperature      | 200 °F                          | 93 °C                         |
| Drying Time             | 2.0 to 3.0 hr                   | 2.0 to 3.0 hr                 |
| Rear Temperature        | 390 to 400 °F                   | 199 to 204 °C                 |
| Middle Temperature      | 400 to 410 °F                   | 204 to 210 °C                 |
| Front Temperature       | 410 to 420 °F                   | 210 to 216 °C                 |
| Nozzle Temperature      | 420 to 430 °F                   | 216 to 221 °C                 |
| Mold Temperature        | 115 to 140 °F                   | 46 to 60 °C                   |
| Back Pressure           | 20.0 to 50.0 psi                | 0.138 to 0.345 MPa            |
| Screw Speed             | 100 to 150 rpm                  | 100 to 150 rpm                |
| Clamp Tonnage           | 2.0 to 3.0 tons/in <sup>2</sup> | 2.8 to 4.1 kN/cm <sup>2</sup> |
| Screw L/D Ratio         | 20.0:1.0                        | 20.0:1.0                      |
| Screw Compression Ratio | 2.0:1.0                         | 2.0:1.0                       |

### Notes

These are typical property values not to be construed as specification limits.

### Processing Techniques

Specific recommendations for resin type and processing conditions can only be made when the end use, required properties and fabrication equipment are known.

### Product Storage and Handling

- Product should be stored in dry conditions at temperatures below 50°C and protected from UV-light
- Improper storage may bring damage to the packaging and can negatively affects on the quality of this product
- Keep material completely dry for good processing

### Company Information

For further information regarding the LyondellBasell company, please visit <http://www.lyb.com/>.

© LyondellBasell Industries Holdings, B.V. 2024

### Disclaimer

Information in this document is accurate to the best of our knowledge at the date of publication. The document is designed to provide users general information for safe handling, use, processing, storage, transportation, disposal and release and does not constitute any warranty or quality specification, either express or implied, including any warranty of merchantability or fitness for any particular purpose. Users shall determine whether the product is suitable for their use and can be used safely and legally.

In addition to any prohibitions of use specifically noted in this document, LyondellBasell may further prohibit or restrict the sale of its products into certain applications. For further information, please contact a LyondellBasell representative.

### Trademarks

The Trademark referenced within the product name is owned or used by the LyondellBasell family of companies.