

Technical Data Sheet

**Ferrocon EPP99GA02BK**

Polypropylene Copolymer
LyondellBasell Industries
Engineering Plastics

General			
Material Status	• Commercial: Active		
Availability	• Latin America	• North America	
Features	• Copolymer	• Electrically Conductive	
Appearance	• Black		
Forms	• Pellets		
Processing Method	• Injection Molding		
Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density / Specific Gravity	1.03	1.03 g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	0.30 g/10 min	0.30 g/10 min	ASTM D1238
Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Strength (73°F (23°C))	3500 psi	24.1 MPa	ASTM D638
Tensile Elongation (Break, 73°F (23°C))	20 %	20 %	ASTM D638
Flexural Modulus			ASTM D790
1% Secant : 73°F (23°C)	175000 psi	1210 MPa	
Tangent : 73°F (23°C)	190000 psi	1310 MPa	
Flexural Strength (73°F (23°C))	4600 psi	31.7 MPa	ASTM D790
Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Notched Izod Impact (73°F (23°C))	9.5 ft·lb/in	510 J/m	ASTM D256
Gardner Impact (73°F (23°C))	200 in·lb	22.6 J	ASTM D5420
Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Deflection Temperature Under Load			ASTM D648
66 psi (0.45 MPa), Unannealed	270 °F	132 °C	
264 psi (1.8 MPa), Unannealed	135 °F	57.2 °C	
Electrical	Nominal Value (English)	Nominal Value (SI)	Test Method
Surface Resistivity	6.0E+2 ohms	6.0E+2 ohms	ASTM D257
Volume Resistivity	3.0E+2 ohms·cm	3.0E+2 ohms·cm	ASTM D257
Additional Information			
The value listed as Volume Resistivity, ASTM D257, was tested in accordance with ASTM D637.			
The value listed as Surface Resistivity, ASTM D257, was tested in accordance with QARD-17.			
Filler Content, ASTM D2584: 21.0%			

Technical Data Sheet



Ferrocon EPP99GA02BK

Polypropylene Copolymer
LyondellBasell Industries
Engineering Plastics



Injection	Nominal Value (English)	Nominal Value (SI)
Drying Temperature	200 °F	93 °C
Drying Time	2.0 hr	2.0 hr
Rear Temperature	400 to 450 °F	204 to 232 °C
Middle Temperature	420 to 500 °F	216 to 260 °C
Front Temperature	430 to 500 °F	221 to 260 °C
Nozzle Temperature	420 to 500 °F	216 to 260 °C
Mold Temperature	80 to 150 °F	27 to 66 °C
Back Pressure	20.0 to 50.0 psi	0.138 to 0.345 MPa
Screw Speed	40 to 100 rpm	40 to 100 rpm
Clamp Tonnage	2.0 to 3.0 tons/in ²	2.8 to 4.1 kN/cm ²
Screw L/D Ratio	20.0:1.0	20.0:1.0
Screw Compression Ratio	2.0:1.0	2.0:1.0

Notes

These are typical property values not to be construed as specification limits.

Processing Techniques

Specific recommendations for resin type and processing conditions can only be made when the end use, required properties and fabrication equipment are known.

Product Storage and Handling

- Product should be stored in dry conditions at temperatures below 50°C and protected from UV-light
- Improper storage may bring damage to the packaging and can negatively affects on the quality of this product
- Keep material completely dry for good processing

Company Information

For further information regarding the LyondellBasell company, please visit <http://www.lyb.com/>.

© LyondellBasell Industries Holdings, B.V. 2024

Disclaimer

Information in this document is accurate to the best of our knowledge at the date of publication. The document is designed to provide users general information for safe handling, use, processing, storage, transportation, disposal and release and does not constitute any warranty or quality specification, either express or implied, including any warranty of merchantability or fitness for any particular purpose. Users shall determine whether the product is suitable for their use and can be used safely and legally.

In addition to any prohibitions of use specifically noted in this document, LyondellBasell may further prohibit or restrict the sale of its products into certain applications. For further information, please contact a LyondellBasell representative.

Trademarks

The Trademark referenced within the product name is owned or used by the LyondellBasell family of companies.