

Technical Data Sheet

**Polyflam Ferro PP NPP00GT01NA**

Polypropylene
LyondellBasell Industries
Engineering Plastics

General

Material Status	• Commercial: Active	
Availability	• Latin America	• North America
Additive	• Flame Retardant	
Features	• Flame Retardant	• Ignition Resistant
Appearance	• Natural Color	
Forms	• Pellets	
Processing Method	• Injection Molding	

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density / Specific Gravity	0.950	0.948 g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	12 g/10 min	12 g/10 min	ASTM D1238
Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Strength (73°F (23°C))	4400 psi	30.3 MPa	ASTM D638
Tensile Elongation (Break, 73°F (23°C))	35 %	35 %	ASTM D638
Flexural Modulus			ASTM D790
1% Secant : 73°F (23°C)	172000 psi	1190 MPa	
Tangent : 73°F (23°C)	187000 psi	1290 MPa	
Flexural Strength (73°F (23°C))	5500 psi	37.9 MPa	ASTM D790
Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Notched Izod Impact (73°F (23°C))	1.0 ft-lb/in	53 J/m	ASTM D256
Unnotched Izod Impact (73°F (23°C))	15 ft-lb/in	800 J/m	ASTM D4812
Gardner Impact (73°F (23°C))	175 in-lb	19.8 J	ASTM D5420
Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Deflection Temperature Under Load			ASTM D648
66 psi (0.45 MPa), Unannealed	200 °F	93.3 °C	
264 psi (1.8 MPa), Unannealed	125 °F	51.7 °C	
RTI Elec (0.13 in (3.2 mm))	149 °F	65.0 °C	UL 746B
RTI Imp (0.13 in (3.2 mm))	149 °F	65.0 °C	UL 746B
RTI Str (0.13 in (3.2 mm))	149 °F	65.0 °C	UL 746B
Electrical	Nominal Value (English)	Nominal Value (SI)	Test Method
Arc Resistance	124 sec	124 sec	ASTM D495
Comparative Tracking Index (CTI)	600 V	600 V	UL 746A
High Voltage Arc Tracking Rate (HVTR)	0.00 in/min	0.00 mm/min	UL 746A
Hot-wire Ignition (HWI)	50 sec	50 sec	UL 746A
Flammability	Nominal Value (English)	Nominal Value (SI)	Test Method
Flame Rating (0.13 in (3.2 mm), NA)	V-2	V-2	UL 94

Additional Information

The value listed as Comparative Track Index, UL 746, was tested in accordance with ASTM D3638.
The value listed as Unnotched Izod Impact, ASTM D256, was tested in accordance with ASTM D4812.

Technical Data Sheet



Polyflam Ferro PP NPP00GT01NA

Polypropylene
LyondellBasell Industries
Engineering Plastics



Injection	Nominal Value (English)	Nominal Value (SI)
Drying Temperature	176 °F	80 °C
Drying Time	2.0 to 3.0 hr	2.0 to 3.0 hr
Processing (Melt) Temp	350 to 440 °F	177 to 227 °C
Mold Temperature	86 to 140 °F	30 to 60 °C

Notes

These are typical property values not to be construed as specification limits.

Processing Techniques

Specific recommendations for resin type and processing conditions can only be made when the end use, required properties and fabrication equipment are known.

Product Storage and Handling

- Product should be stored in dry conditions at temperatures below 50°C and protected from UV-light
- Improper storage may bring damage to the packaging and can negatively affects on the quality of this product
- Keep material completely dry for good processing

Company Information

For further information regarding the LyondellBasell company, please visit <http://www.lyb.com/>.

© LyondellBasell Industries Holdings, B.V. 2024

Disclaimer

Information in this document is accurate to the best of our knowledge at the date of publication. The document is designed to provide users general information for safe handling, use, processing, storage, transportation, disposal and release and does not constitute any warranty or quality specification, either express or implied, including any warranty of merchantability or fitness for any particular purpose. Users shall determine whether the product is suitable for their use and can be used safely and legally.

In addition to any prohibitions of use specifically noted in this document, LyondellBasell may further prohibit or restrict the sale of its products into certain applications. For further information, please contact a LyondellBasell representative.

Trademarks

The Trademark referenced within the product name is owned or used by the LyondellBasell family of companies.