

Technical Data Sheet

**Ferro Pp TPP05AF61HB**

Polypropylene Homopolymer
LyondellBasell Industries
Engineering Plastics

General

Material Status	• Commercial: Active	
Availability	• Latin America	• North America
Filler / Reinforcement	• Talc, 5.0% Filler by Weight	
Features	• Homopolymer	
Appearance	• White	
Forms	• Pellets	
Processing Method	• Injection Molding	

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density / Specific Gravity	0.950	0.948 g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	13 g/10 min	13 g/10 min	ASTM D1238
Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Strength (Yield, 73°F (23°C))	5500 psi	37.9 MPa	ASTM D638
Tensile Elongation (Break, 73°F (23°C))	12 %	12 %	ASTM D638
Flexural Modulus			ASTM D790
1% Secant : 73°F (23°C)	313000 psi	2160 MPa	
Tangent : 73°F (23°C)	322000 psi	2220 MPa	
Flexural Strength (Yield, 73°F (23°C))	8600 psi	59.3 MPa	ASTM D790
Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Notched Izod Impact (73°F (23°C))	0.70 ft·lb/in	37 J/m	ASTM D256
Unnotched Izod Impact (73°F (23°C))	8.1 ft·lb/in	430 J/m	ASTM D4812
Gardner Impact	3.00 in·lb	0.339 J	ASTM D5420
Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Deflection Temperature Under Load			ASTM D648
66 psi (0.45 MPa), Unannealed	255 °F	124 °C	
264 psi (1.8 MPa), Unannealed	155 °F	68.3 °C	

Additional Information

Filler Content, ASTM D2584: 5%

Technical Data Sheet



Ferro Pp TPP05AF61HB

Polypropylene Homopolymer
LyondellBasell Industries
Engineering Plastics



Injection	Nominal Value (English)	Nominal Value (SI)
Drying Temperature	176 °F	80 °C
Drying Time	2.0 to 3.0 hr	2.0 to 3.0 hr
Processing (Melt) Temp	428 to 500 °F	220 to 260 °C
Mold Temperature	86 to 140 °F	30 to 60 °C

Notes

These are typical property values not to be construed as specification limits.

Processing Techniques

Specific recommendations for resin type and processing conditions can only be made when the end use, required properties and fabrication equipment are known.

Product Storage and Handling

- Product should be stored in dry conditions at temperatures below 50°C and protected from UV-light
- Improper storage may bring damage to the packaging and can negatively affects on the quality of this product
- Keep material completely dry for good processing

Company Information

For further information regarding the LyondellBasell company, please visit <http://www.lyb.com/>.

© LyondellBasell Industries Holdings, B.V. 2024

Disclaimer

Information in this document is accurate to the best of our knowledge at the date of publication. The document is designed to provide users general information for safe handling, use, processing, storage, transportation, disposal and release and does not constitute any warranty or quality specification, either express or implied, including any warranty of merchantability or fitness for any particular purpose. Users shall determine whether the product is suitable for their use and can be used safely and legally.

In addition to any prohibitions of use specifically noted in this document, LyondellBasell may further prohibit or restrict the sale of its products into certain applications. For further information, please contact a LyondellBasell representative.

Trademarks

The Trademark referenced within the product name is owned or used by the LyondellBasell family of companies.