

Technical Data Sheet

**Fiberfil J-60/10/CC/30/E NATL**

Polypropylene Homopolymer
LyondellBasell Industries
Engineering Plastics

General

Material Status	• Commercial: Active
Availability	• North America
Filler / Reinforcement	• Calcium Carbonate, 30% Filler by Weight • Glass Fiber, 10% Filler by Weight
Features	• Chemically Coupled • Homopolymer
Appearance	• Natural Color
Forms	• Pellets

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density	1.23 g/cm ³	1.23 g/cm ³	ISO 1183/A
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	7.0 g/10 min	7.0 g/10 min	ASTM D1238
Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Stress (Yield)	5080 psi	35.0 MPa	ISO 527-2
Tensile Strain (Yield, 73°F (23°C))	4.0 %	4.0 %	ISO 527-2
Flexural Modulus (73°F (23°C))	363000 psi	2500 MPa	ISO 178
Flexural Stress (73°F (23°C))	9430 psi	65.0 MPa	ISO 178
Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Notched Izod Impact Strength (73°F (23°C))	2.4 ft·lb/in ²	5.0 kJ/m ²	ISO 180/1A

Technical Data Sheet



Fiberfil J-60/10/CC/30/E NATL

Polypropylene Homopolymer
LyondellBasell Industries
Engineering Plastics



Injection	Nominal Value (English)	Nominal Value (SI)
Drying Temperature	170 °F	77 °C
Drying Time	2.0 hr	2.0 hr
Suggested Max Moisture	0.20 %	0.20 %
Rear Temperature	390 to 410 °F	199 to 210 °C
Middle Temperature	400 to 440 °F	204 to 227 °C
Front Temperature	360 to 390 °F	182 to 199 °C
Nozzle Temperature	360 to 380 °F	182 to 193 °C
Processing (Melt) Temp	390 to 450 °F	199 to 232 °C
Mold Temperature	90 to 160 °F	32 to 71 °C
Injection Rate	Slow-Moderate	Slow-Moderate
Back Pressure	0.00 to 100 psi	0.00 to 0.689 MPa

Injection Notes

Screw speed: Medium

Notes

These are typical property values not to be construed as specification limits.

Processing Techniques

Specific recommendations for resin type and processing conditions can only be made when the end use, required properties and fabrication equipment are known.

Product Storage and Handling

- Product should be stored in dry conditions at temperatures below 50°C and protected from UV-light
- Improper storage may bring damage to the packaging and can negatively affects on the quality of this product
- Keep material completely dry for good processing

Company Information

For further information regarding the LyondellBasell company, please visit <http://www.lyb.com/>.

© LyondellBasell Industries Holdings, B.V. 2024

Disclaimer

Information in this document is accurate to the best of our knowledge at the date of publication. The document is designed to provide users general information for safe handling, use, processing, storage, transportation, disposal and release and does not constitute any warranty or quality specification, either express or implied, including any warranty of merchantability or fitness for any particular purpose. Users shall determine whether the product is suitable for their use and can be used safely and legally.

In addition to any prohibitions of use specifically noted in this document, LyondellBasell may further prohibit or restrict the sale of its products into certain applications. For further information, please contact a LyondellBasell representative.

Trademarks

The Trademark referenced within the product name is owned or used by the LyondellBasell family of companies.

Page: 2 of 2
LyondellBasell

www.lyondellbasell.com
Publish Date: 2024-03-14