

Technical Data Sheet

**Fiberfil PP-61/V2**

Polypropylene Copolymer
LyondellBasell Industries
Engineering Plastics

General			
Material Status	• Commercial: Active		
Availability	• North America		
Features	• Copolymer		• Flame Retardant
Forms	• Pellets		
Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density / Specific Gravity	0.940	0.938 g/cm³	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	20 g/10 min	20 g/10 min	ASTM D1238
Water Absorption (24 hr)	0.020 %	0.020 %	ASTM D570
Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Modulus (73°F (23°C))	190000 psi	1310 MPa	ASTM D638
Tensile Strength (73°F (23°C))	4000 psi	27.6 MPa	ASTM D638
Tensile Elongation (Yield, 73°F (23°C))	25 %	25 %	ASTM D638
Flexural Modulus - Tangent (73°F (23°C))	170000 psi	1170 MPa	ASTM D790
Flexural Strength (73°F (23°C))	4600 psi	31.7 MPa	ASTM D790
Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Notched Izod Impact			ASTM D256
73°F (23°C), 0.125 in (3.18 mm)	1.8 ft-lb/in	96 J/m	
Hardness	Nominal Value (English)	Nominal Value (SI)	Test Method
Rockwell Hardness (R-Scale)	85 to 90	85 to 90	ASTM D785
Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Deflection Temperature Under Load			ASTM D648
66 psi (0.45 MPa), Unannealed	160 °F	71.1 °C	
264 psi (1.8 MPa), Unannealed	145 °F	62.8 °C	
Flammability	Nominal Value (English)	Nominal Value (SI)	Test Method
Flame Rating (0.06 in (1.5 mm))	V-2	V-2	UL 94

Technical Data Sheet



Fiberfil PP-61/V2

Polypropylene Copolymer
LyondellBasell Industries
Engineering Plastics



Injection	Nominal Value (English)	Nominal Value (SI)
Drying Temperature	170 °F	77 °C
Drying Time	2.0 hr	2.0 hr
Suggested Max Moisture	0.20 %	0.20 %
Rear Temperature	360 to 390 °F	182 to 199 °C
Middle Temperature	380 to 410 °F	193 to 210 °C
Front Temperature	370 to 400 °F	188 to 204 °C
Nozzle Temperature	360 to 380 °F	182 to 193 °C
Processing (Melt) Temp	380 to 420 °F	193 to 216 °C
Mold Temperature	90 to 160 °F	32 to 71 °C
Injection Rate	Slow-Moderate	Slow-Moderate
Back Pressure	0.00 to 100 psi	0.00 to 0.689 MPa

Injection Notes

Screw speed: Slow to Medium

Notes

These are typical property values not to be construed as specification limits.

Processing Techniques

Specific recommendations for resin type and processing conditions can only be made when the end use, required properties and fabrication equipment are known.

Product Storage and Handling

- Product should be stored in dry conditions at temperatures below 50°C and protected from UV-light
- Improper storage may bring damage to the packaging and can negatively affects on the quality of this product
- Keep material completely dry for good processing

Company Information

For further information regarding the LyondellBasell company, please visit <http://www.lyb.com/>.

© LyondellBasell Industries Holdings, B.V. 2024

Disclaimer

Information in this document is accurate to the best of our knowledge at the date of publication. The document is designed to provide users general information for safe handling, use, processing, storage, transportation, disposal and release and does not constitute any warranty or quality specification, either express or implied, including any warranty of merchantability or fitness for any particular purpose. Users shall determine whether the product is suitable for their use and can be used safely and legally.

In addition to any prohibitions of use specifically noted in this document, LyondellBasell may further prohibit or restrict the sale of its products into certain applications. For further information, please contact a LyondellBasell representative.

Trademarks

The Trademark referenced within the product name is owned or used by the LyondellBasell family of companies.

Page: 2 of 2
LyondellBasell

www.lyondellbasell.com
Publish Date: 2024-03-14