

## Technical Data Sheet

**Gapex RPP15EU57HB BLACK**

Polypropylene  
LyondellBasell Industries  
Engineering Plastics

**General**

|                        |                                        |
|------------------------|----------------------------------------|
| Material Status        | • Commercial: Active                   |
| Availability           | • Latin America • North America        |
| Filler / Reinforcement | • Glass Fiber, 16% Filler by Weight    |
| Additive               | • Impact Modifier                      |
| Features               | • Chemically Coupled • Impact Modified |
| Appearance             | • Black                                |
| Forms                  | • Pellets                              |

| Physical                                  | Nominal Value (English) | Nominal Value (SI)     | Test Method |
|-------------------------------------------|-------------------------|------------------------|-------------|
| Density / Specific Gravity                | 1.01                    | 1.01 g/cm <sup>3</sup> | ASTM D792   |
| Melt Mass-Flow Rate (MFR) (230°C/2.16 kg) | 7.0 g/10 min            | 7.0 g/10 min           | ASTM D1238  |
| Mechanical                                | Nominal Value (English) | Nominal Value (SI)     | Test Method |
| Tensile Strength (73°F (23°C))            | 6800 psi                | 46.9 MPa               | ASTM D638   |
| Tensile Elongation (Break, 73°F (23°C))   | 6.0 %                   | 6.0 %                  | ASTM D638   |
| Flexural Modulus                          |                         |                        | ASTM D790   |
| 1% Secant : 73°F (23°C)                   | 372000 psi              | 2560 MPa               |             |
| Tangent : 73°F (23°C)                     | 415000 psi              | 2860 MPa               |             |
| Flexural Strength (73°F (23°C))           | 10500 psi               | 72.4 MPa               | ASTM D790   |
| Impact                                    | Nominal Value (English) | Nominal Value (SI)     | Test Method |
| Notched Izod Impact (73°F (23°C))         | 2.2 ft·lb/in            | 120 J/m                | ASTM D256   |
| Unnotched Izod Impact (73°F (23°C))       | 9.3 ft·lb/in            | 500 J/m                | ASTM D4812  |
| Gardner Impact (73°F (23°C))              | 10.0 in·lb              | 1.13 J                 | ASTM D5420  |
| Thermal                                   | Nominal Value (English) | Nominal Value (SI)     | Test Method |
| Deflection Temperature Under Load         |                         |                        | ASTM D648   |
| 66 psi (0.45 MPa), Unannealed             | 300 °F                  | 149 °C                 |             |
| 264 psi (1.8 MPa), Unannealed             | 260 °F                  | 127 °C                 |             |

**Additional Information**

Testing and measurements were performed at 73 +/-3°F and 50 +/-5% relative humidity unless otherwise noted.

## Technical Data Sheet



# Gapex RPP15EU57HB BLACK

Polypropylene  
LyondellBasell Industries  
Engineering Plastics



| Injection              | Nominal Value (English) | Nominal Value (SI) |
|------------------------|-------------------------|--------------------|
| Drying Temperature     | 160 to 180 °F           | 71 to 82 °C        |
| Drying Time            | 2.0 to 4.0 hr           | 2.0 to 4.0 hr      |
| Rear Temperature       | 430 to 460 °F           | 221 to 238 °C      |
| Middle Temperature     | 440 to 470 °F           | 227 to 243 °C      |
| Front Temperature      | 450 to 500 °F           | 232 to 260 °C      |
| Nozzle Temperature     | 450 to 500 °F           | 232 to 260 °C      |
| Processing (Melt) Temp | 430 to 460 °F           | 221 to 238 °C      |
| Mold Temperature       | 100 to 150 °F           | 38 to 66 °C        |
| Injection Rate         | Slow-Moderate           | Slow-Moderate      |
| Back Pressure          | 20.0 to 50.0 psi        | 0.138 to 0.345 MPa |
| Cushion                | 0.200 to 0.500 in       | 5.08 to 12.7 mm    |

### Notes

These are typical property values not to be construed as specification limits.

### Processing Techniques

Specific recommendations for resin type and processing conditions can only be made when the end use, required properties and fabrication equipment are known.

### Product Storage and Handling

- Product should be stored in dry conditions at temperatures below 50°C and protected from UV-light
- Improper storage may bring damage to the packaging and can negatively affects on the quality of this product
- Keep material completely dry for good processing

### Company Information

For further information regarding the LyondellBasell company, please visit <http://www.lyb.com/>.

© LyondellBasell Industries Holdings, B.V. 2024

### Disclaimer

Information in this document is accurate to the best of our knowledge at the date of publication. The document is designed to provide users general information for safe handling, use, processing, storage, transportation, disposal and release and does not constitute any warranty or quality specification, either express or implied, including any warranty of merchantability or fitness for any particular purpose. Users shall determine whether the product is suitable for their use and can be used safely and legally.

In addition to any prohibitions of use specifically noted in this document, LyondellBasell may further prohibit or restrict the sale of its products into certain applications. For further information, please contact a LyondellBasell representative.

### Trademarks

The Trademark referenced within the product name is owned or used by the LyondellBasell family of companies.