

Technical Data Sheet



Gapex RPP20EB82HB BLACK

Polypropylene Homopolymer
LyondellBasell Industries
Engineering Plastics

General			
Material Status	• Commercial: Active		
Availability	• Latin America	• North America	
Filler / Reinforcement	• Glass Fiber, 20% Filler by Weight		
Features	• Chemically Coupled		
Appearance	• Black		
Forms	• Pellets		
Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density / Specific Gravity	1.05	1.05 g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	4.5 g/10 min	4.5 g/10 min	ASTM D1238
Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Strength (73°F (23°C))	10300 psi	71.0 MPa	ASTM D638
Tensile Elongation (Break, 73°F (23°C))	5.0 %	5.0 %	ASTM D638
Flexural Modulus			ASTM D790
1% Secant : 73°F (23°C)	541000 psi	3730 MPa	
Tangent : 73°F (23°C)	566000 psi	3900 MPa	
Flexural Strength (73°F (23°C))	15400 psi	106 MPa	ASTM D790
Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Notched Izod Impact (73°F (23°C))	1.8 ft·lb/in	96 J/m	ASTM D256
Unnotched Izod Impact (73°F (23°C))	11 ft·lb/in	570 J/m	ASTM D4812
Gardner Impact (73°F (23°C))	5.00 in·lb	0.565 J	ASTM D5420
Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Deflection Temperature Under Load			ASTM D648
66 psi (0.45 MPa), Unannealed	320 °F	160 °C	
264 psi (1.8 MPa), Unannealed	295 °F	146 °C	
Additional Information			
Testing and measurements were performed at 73 +/-3°F and 50 +/-5% relative humidity unless otherwise noted.			

Technical Data Sheet



Gapex RPP20EB82HB BLACK

Polypropylene Homopolymer
LyondellBasell Industries
Engineering Plastics



Injection	Nominal Value (English)	Nominal Value (SI)
Drying Temperature	160 to 180 °F	71 to 82 °C
Drying Time	2.0 to 4.0 hr	2.0 to 4.0 hr
Rear Temperature	430 to 460 °F	221 to 238 °C
Middle Temperature	440 to 470 °F	227 to 243 °C
Front Temperature	450 to 500 °F	232 to 260 °C
Nozzle Temperature	450 to 500 °F	232 to 260 °C
Processing (Melt) Temp	430 to 460 °F	221 to 238 °C
Mold Temperature	100 to 150 °F	38 to 66 °C
Injection Rate	Slow-Moderate	Slow-Moderate
Back Pressure	20.0 to 50.0 psi	0.138 to 0.345 MPa
Cushion	0.200 to 0.500 in	5.08 to 12.7 mm

Notes

These are typical property values not to be construed as specification limits.

Processing Techniques

Specific recommendations for resin type and processing conditions can only be made when the end use, required properties and fabrication equipment are known.

Product Storage and Handling

- Product should be stored in dry conditions at temperatures below 50°C and protected from UV-light
- Improper storage may bring damage to the packaging and can negatively affects on the quality of this product
- Keep material completely dry for good processing

Company Information

For further information regarding the LyondellBasell company, please visit <http://www.lyb.com/>.

© LyondellBasell Industries Holdings, B.V. 2024

Disclaimer

Information in this document is accurate to the best of our knowledge at the date of publication. The document is designed to provide users general information for safe handling, use, processing, storage, transportation, disposal and release and does not constitute any warranty or quality specification, either express or implied, including any warranty of merchantability or fitness for any particular purpose. Users shall determine whether the product is suitable for their use and can be used safely and legally.

In addition to any prohibitions of use specifically noted in this document, LyondellBasell may further prohibit or restrict the sale of its products into certain applications. For further information, please contact a LyondellBasell representative.

Trademarks

The Trademark referenced within the product name is owned or used by the LyondellBasell family of companies.