



Hifax BA35H

Compounded Polyolefin

Product Description

Hifax BA35H conventional melt flow, 1,000 MPa flexural modulus, UL 94 V-2 flame retardant polypropylene copolymer has an excellent combination of properties and processability. It was designed for applications that require flame and heat resistance, along with good electrical properties, high impact strength and good surface quality.

Product Characteristics

Status	Commercial: Active
Test Method used	ASTM
Availability	North America, Asia-Pacific, Australia/NZ, Africa-Middle East, Latin America
Processing Methods	Injection Molding
Features	Good Colorability, Copolymer, Good Corrosion Resistance, Good Electrical Properties, Flame Retardant, Medium Flow, High Heat Resistance, Good Impact Resistance, Good Processability, Good Surface Finish
Typical Customer Applications	Battery Cases, Furniture, Hair Dryers, Shavers and Steam Irons, Housewares, Other Industrial

Typical Properties	Method	Value Unit
Physical		
Melt Flow Rate (230°C/2.16kg)	ASTM D 1238	4 g/10 min
Mechanical		
Flexural Modulus	ASTM D 790	1000 MPa
Tensile Strength @ Yield	ASTM D 638	27 MPa
Tensile Elongation @ Brk	ASTM D 638	85 %
Impact		
Notched Izod Impact (23 °C)	ASTM D 256	130 J/m
Hardness		
Rockwell Hardness (R-Scale)	ASTM D 785	85
Thermal		
DTUL @66psi - Unannealed	ASTM D 648	88 °C
Electrical		
Dielectric strength	ASTM D 149	690 V/mil
Volume Resistivity	ASTM D 257	8.9E+016 ohm-cm
Arc resistance	ASTM D 495	133
Additional Information		
Mold shrink, Linear-Flow	ASTM D 955	1.5 %
<i>Note: After 48 hrs at 23°C (Tool).</i>		
Limiting Oxygen Index	ASTM D 2863	28 %

Additional Properties

Note: Mold shrinkage values are determined on laboratory injection molded 100 mm x 150 mm x 3.2 mm plaques and, as such, are not necessarily representative of actual field data. Since, for example, wall thickness, gate type and location, flow length and paint oven temperature affect final part dimensions, it is recommended that you contact your Basell representative before any tools are cut.

Notes

Typical properties; not to be construed as specifications.

© LyondellBasell Industries Holdings, B.V. 2014

LyondellBasell markets this product through the following entities:

- ┆ Equistar Chemicals, LP
- ┆ Basell Sales & Marketing Company B.V.
- ┆ Basell Asia Pacific Limited
- ┆ Basell International Trading FZE
- ┆ LyondellBasell Australia Pty Ltd

For the contact details of the LyondellBasell company selling this product in your country, please visit <http://www.lyondellbasell.com/>.

Before using a product sold by a company of the LyondellBasell family of companies, users should make their own independent determination that the product is suitable for the intended use and can be used safely and legally. SELLER MAKES NO WARRANTY; EXPRESS OR IMPLIED (INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE OR ANY WARRANTY) OTHER THAN AS SEPARATELY AGREED TO BY THE PARTIES IN A CONTRACT.

This product(s) may not be used in: (i) any U.S. FDA Class I, Health Canada Class I, and/or European

Union Class I medical devices, without prior notification to Seller for each specific product and application; or (ii) the manufacture of any of the following, without prior written approval by Seller for each specific product and application: U.S. FDA Class II Medical Devices; Health Canada Class II or Class III Medical Devices; European Union Class II Medical Devices; film, overwrap and/or product packaging that is considered a part or component of one of the aforementioned medical devices; packaging in direct contact with a pharmaceutical active ingredient and/or dosage form that is intended for inhalation, injection, intravenous, nasal, ophthalmic (eye), digestive, or topical (skin) administration; and tobacco related products and applications. Additionally, the product(s) may not be used in: (i) U.S. FDA Class III Medical Devices; Health Canada Class IV Medical Devices; European Class III Medical Devices; (ii) applications involving permanent implantation into the body; (iii) life-sustaining medical applications; and (iv) lead, asbestos or MTBE related applications. All references to U.S. FDA, Health Canada, and European Union regulations include another country's equivalent regulatory classification.

Users should review the applicable Material Safety Data Sheet before handling the product.

Addhere, Adflex, Adstif, Adsyl, Akoafloor, Akoalit, Alastian, Alathon, Alkylate, Amazing Chemistry, Aquamarine, Aquathene, Arconate, Arcosolv, Arctic Plus, Arctic Shield, Avant, Catalloy, Clyrell, CRP, Crystex, Dexflex, Duopac, Duoprime, Explore & Experiment, Filmex, Flexathene, Fueling the power to win, Get in touch with, Glacido, Hifax, Histif, Hostacom, Hostalen PP, Hostalen ACP, Ideal, Indure, Integrate, Koattro, LIPP, Lucalen, Luflexen, Lupolen, Lupolex, Luposim, Lupostress, Lupotech, Metocene, Microthene, Moplen, MPDIOL, Nerolex, Nexprene, Petrothene, Plexar, Polymeg, Pristene, Prodflex, Pro-fax, Punctilious, Purell, Refax, SAA100, SAA101, Sequel, Softell, Spherilene, Spheripol, Spherizone, Starflex, Stretchene, Superflex, TBAC, Tebol, T-Hydro, Toppyl, Trans4m, Tufflo, Ultrathene, Vacido and Valtec, are trademarks owned and/or used by the LyondellBasell family of companies.

Adsyl, Akoafloor, Akoalit, Alastian, Alathon, Aquamarine, Arconate, Arcosolv, Arctic Plus, Arctic Shield, Avant, CRP, Crystex, Dexflex, Duopac, Duoprime, Explore & Experiment, Filmex, Flexathene, Hifax, Hostacom, Hostalen, Ideal, Integrate, Koattro, Lucalen, Lupolen, Microthene, Moplen, MPDIOL, Nexprene, Petrothene, Plexar, Polymeg, Pristene, Pro-fax, Punctilious, Purell, Sequel, Softell, Spheripol, Spherizone, Starflex, Tebol, T-Hydro, Toppyl, Tufflo and Ultrathene are registered in the U.S. Patent and Trademark Office.

Release Date: 01 Feb 2004