



Hifax HX TRC 135X / 6

Compounded Polyolefin

Product Description

PP/EPR-Blend, 20% mineralfilled, impact modified, with ultra low shrinkage and high flowability for painted exterior applications. Contains a advanced demoulding package for improved processing.

Product Characteristics

Status	Commercial: Active
Test Method used	ISO
Features	High Flow , Paintable, Low Shrinkage, Impact Modified
Typical Customer Applications	Exterior Applications

Typical Properties	Method	Value Unit
Physical		
Density (Method A)	ISO 1183	1.05 g/cm³
Melt flow rate (MFR) (230°C/2.16Kg)	ISO 1133	11 g/10 min
Mechanical		
Tensile Modulus (23 °C, 50 mm/min)	ISO 527-1, -2	1400 MPa
Tensile Stress at Yield (23 °C, 50 mm/min)	ISO 527-1, -2	17.0 MPa
Tensile Strain at Break (23 °C, 50 mm/min)	ISO 527-1, -2	550 %
Flexural modulus (23 °C, 2 mm/min)	ISO 178	1350 MPa
Impact		
Charpy unnotched impact strength (23 °C)	ISO 179	No Break kJ/m²
(-30 °C)		No Break kJ/m²
Charpy notched impact strength (23 °C, Edgewise, Notch A)	ISO 179	72 kJ/m²
(-30 °C, Edgewise, Notch A)		10 kJ/m²
Thermal		
Heat deflection temperature B (0.45 MPa) Unannealed	ISO 75B-1, -2	95 °C
Vicat softening temperature (A50 (50°C/h 10N))	ISO 306	110 °C

Additional Properties

CLTE, DIN 53752, 23 to 80°C: 4.3e-5 1/K

Notes

Typical properties; not to be construed as specifications.

© LyondellBasell Industries Holdings, B.V. 2011

LyondellBasell markets this product through the following entities:

Equistar Chemicals, LP
Basell Sales & Marketing Company B.V.
Basell Asia Pacific Limited
Basell International Trading FZE
LyondellBasell Australia Pty Ltd

For the contact details of the LyondellBasell company selling this product in your country, please visit <http://www.lyondellbasell.com/>.

Before using a product sold by one of the LyondellBasell family of companies, users should make their own independent determination that the product is suitable for the intended use and can be used safely and legally. SELLER MAKES NO WARRANTY; EXPRESS OR IMPLIED (INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE) OTHER THAN AS SEPARATELY AGREED BETWEEN THE PARTIES IN WRITING. This product(s) may not be used in the manufacture of any US FDA Class III Medical Device or Health Canada Class IV Medical Device and may not be used in the manufacture of any US FDA Class II Medical Device or Health Canada Class II or Class III Medical Device without the prior written approval by Seller of each specific product or application.

Users should review the applicable Material Safety Data Sheet before handling the product.

Adflex, Adstif, Adsyl, Akoafloor, Akoalit, Alastian, Alathon, Alkylate, Amazing Chemistry, Aquamarine, Aquathene, Arconate, Arcopure, Arcosolv, Arctic Plus, Arctic Shield, Avant, Catalloy, Clyrell, CRP, Crystex, Dexflex, Duopac, Duoprime, Explore & Experiment, Filmex, Flexathene, Fueling the Power to Win, Get in touch with, Glacido, Hifax, Histif, Hostacom, Hostalen, Ideal, Integrate, Koattro, LIPP, Lucalen, Luflexen, Lupolen, Lupolex, Luposim, Lupostress, Lupotech, Metocene, Microthene, Moplen, MPDIOL, Nerolex, Nexprene, Petrothene, Plexar, Polymeg, Pristene, Prodflex, Pro-Fax, Punctilious, Purell, SAA100, SAA101, Sequel, Softell, Spherilene, Spheripol, Spherizone, Starflex, Stretchene, Superflex, TBAC, Tebol, T-Hydro, Toppyl, Trans4m, Tufflo, Ultrathene, Vacido and Valtec are trademarks owned or used by the LyondellBasell family of companies.

Adsyl, Akoafloor, Akoalit, Alastian, Alathon, Aquamarine, Arconate, Arcopure, Arcosolv, Arctic Plus, Arctic Shield, Avant, Clyrell, CRP, Crystex, Dexflex, Duopac, Duoprime, Explore & Experiment, Filmex,

Flexathene, Hifax, Hostacom, Hostalen, Ideal, Integrate, Koattro, Lucalen, Lupolen, Microthene, Moplen, MPDIOL, Nexprene, Petrothene, Plexar, Polymeg, Pristene, Pro-Fax, Punctilious, Purell, Sequel, Softell, Spheripol, Spherizone, Starflex, Tebol, T-Hydro, Toppyl, Tufflo and Ultrathene are registered in the U.S. Patent and Trademark Office.

Release Date: 04 May 2011

