



Hifax TRC 221P 2

Compounded Polyolefin

Product Description

"Hifax" TRC 221P 2 is a new high melt flow, 20% mineral filled polypropylene copolymer for injection moulding. It combines a very high flowability with an excellent impact/stiffness balance and very low CLTE. The grade has been specifically designed for moulding of large complex parts that require high impact strength as well as good stiffness. This grade is available in custom colour, pellet form. It contains UV stabiliser for usage in unpainted parts

Product Characteristics

Status	Commercial: Active
Test Method used	ISO
Availability	Europe
Features	Copolymer, High Flow , Good Impact Resistance , Good Stiffness
Typical Customer Applications	Exterior Applications, Bumpers

Typical Properties	Method	Value Unit
Physical		
Density (Method A)	ISO 1183	1.05 g/cm³
Melt flow rate (MFR) (230°C/2.16Kg)	ISO 1133	17 g/10 min
Mechanical		
Tensile Stress at Yield	ISO 527-1, -2	17.0 MPa
Flexural modulus	ISO 178	1600 MPa
Impact		
Notched izod impact strength	ISO 180	
(- 30 °C, Type 1, Notch A)		5.5 kJ/m²
(23 °C, Type 1, Notch A)		45 No kJ/m² Break
Thermal		
Heat deflection temperature B (0.45 MPa) Unannealed	ISO 75B-1, -2	100 °C
Heat deflection temperature A (1.80 MPa) Unannealed	ISO 75A-1, -2	55 °C
Vicat softening temperature B/50	ISO 306	48 °C

Notes

Typical properties; not to be construed as specifications.

© LyondellBasell Industries Holdings, B.V. 2010

For the contact details of the LyondellBasell company selling this product in your country, please visit <http://www.lyondellbasell.com/>.

Before using a product sold by one of the LyondellBasell family of companies, users should make their own independent determination that the product is suitable for the intended use and can be used safely and legally. SELLER MAKES NO WARRANTY; EXPRESS OR IMPLIED (INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE) OTHER THAN AS SEPARATELY AGREED BETWEEN THE PARTIES IN WRITING. This product(s) may not be used in the manufacture of any US FDA Class III Medical Device or Health Canada Class IV Medical Device and may not be used in the manufacture of any US FDA Class II Medical Device or Health Canada Class II or Class III Medical Device without the prior written approval by Seller of each specific product or application.

Users should review the applicable Material Safety Data Sheet before handling the product.

Adflex, Adstif, Adsyl, Akoafloor, Akoalit, Alastian, Alathon, Alkylate, Aquamarine, Aquathene, Arconate, Arcopure, Arcosolv, Arctic Plus, Arctic Shield, Avant, Catalloy, Clyrell, CRP, Crystex, Dexflex, Duopac, Duoprime, Duotreat, Filmex, Flexathene, Get in touch with, Glacido, Glidox, Glidsol, Hifax, Histif, Hostacom, Hostalen PP, Hostalen ACP, Ideal, Indure, Integrate, Koattro, LIPP, Lucalen, Luflexen, Lupocomp, Lupolen, Lupolex, Luposim, Lupostress, Lupotech, Metocene, Microthene, Moplen, MPDIOL, Navacet, Nerolex, Nexprene, Petrothene, Plexar, Polymeg, Pristene, Prodflex, Pro-Fax, Punctilious, Purell, SAA 100, SAA 101, Sequel, Softell, Spherilene, Spheripol, Spherizone, Starflex, Stretchene, Superflex, TBAC, Tebol, Tetralol, T-Hydro, Toppyl, Trans4m, Tufflo, Ultrathene, Vacido, Valtec, and Winsense are trademarks owned and/or used by LyondellBasell group companies.

Akoafloor, Akoalit, Alastian, Alathon, Aquamarine, Arconate, Arcopure, Arcosolv, Arctic Plus, Arctic Shield, Avant, Clyrell, CRP, Crystex, Dexflex, Duopac, Duoprime, Filmex, Flexathene, Glidox, Glidsol, Hifax, Hostacom, Hostalen, Ideal, Indure, Integrate, Koattro, Lucalen, Lupolen, Microthene, Moplen, MPDIOL, Nexprene, Petrothene, Plexar, Polymeg, Pristene, Pro-Fax, Punctilious, Purell, Sequel, Spheripol, Spherizone, Softell, Starflex, Tebol, Tetralol, T-Hydro, Toppyl, Tufflo, Ultrathene, and Winsense are registered in the U.S. Patent and Trademark Office.

Release Date: 13 Feb 2011