



Home / Products & Technology / Polymers / Hostacom 65F4-2C BLK P23726

Hostacom 65F4-2C BLK P23726

Description

Hostacom 65F4-2C BLK P23726 conventional melt flow, 1,900 MPa flexural modulus, 20% talc-filled polypropylene homopolymer resin. It has good impact resistance, dimensional stability, colorability and heat aging performance.

Availability

North America

[» CustomerXpress](#)[» Find a Sales Contact](#)[» Request Product Information](#)

Legend

SDS - Safety Data Sheet

PSB - Product Stewardship Bulletin

[Information](#)[SDS](#)[Safety Summary](#)

Product Data and Technical Information

Typical Properties

Melt Flow Rate (230°C/2.16 kg)	4 g/10 min
Density (23°C)	1.05 g/cm ³
Flexural Modulus	1900 MPa
Tensile Strength at Break	29 MPa
Tensile Strength at Yield	31 MPa
Tensile Elongation at Break	70 %
Tensile Elongation at Yield	4 %
Notched Izod Impact Strength (23°C)	37 J/m
Rockwell Hardness (R-Scale)	84
Deflection Temperature Under Load (66 psi, Unannealed)	109 °C
Mold Shrinkage	

Process

Injection Molding

Resin

Polypropylene Compounds

Applications

Industrial

Prohibited Applications of Compounded Polyolefins:

The use of LyondellBasell Compounded Polyolefins in the following applications is prohibited:

- All parts for Aeronautical use
- All parts for Train transportation use
- Air bag unit housings
- Seat belt systems and mechanisms
- Brake systems and mechanisms
- Pedals (brake, gas, clutch)
- Steering systems and mechanisms
- All parts with flammability requirements for Building and Constructions
- All parts with flammability requirements for Industrial applications use
- All parts for Medical applications use

This site uses cookies. By continuing to browse the site, you agree to our use of cookies.

» ACCEPT

[Privacy](#)