



Hostacom BA742EC

Compounded Polyolefin

Product Description

Hostacom BA742EC low melt flow, 1,200 MPa flexural modulus, precolored, extrusion grade polypropylene copolymer has a good balance of strength, stiffness, impact resistance and processability. It was designed primarily for solar panel and related applications.

Product Characteristics

Status	Commercial: Active
Test Method used	ASTM
Availability	North America, Asia-Pacific, Australia/NZ, Africa-Middle East, Latin America
Processing Method	Extrusion Pipe Sheet and Semi Finished Products
Features	Copolymer, Low Flow , Good Impact Resistance , Good Melt Strength , Good Processability, Good Stiffness , Good Strength
Typical Customer Applications	Panels & Profiles, Soft Profile & Sheets

Typical Properties	Method	Value Unit
Physical		
Density -Specific Gravity	ASTM D 792	0.91 g/cm ³
Melt flow rate (230°C/2.16kg)	ASTM D 1238	1 g/10 min
Mechanical		
Tensile Strength @ Yield	ASTM D 638	25 MPa
Tensile Strength @ Break	ASTM D 638	31 MPa
Flexural Modulus	ASTM D 790	1200 MPa
Tensile Elongation @ Brk	ASTM D 638	700 %
Impact		
Notched izod impact (23 °C)	ASTM D 256	800 J/m

Notes

Typical properties; not to be construed as specifications.

© LyondellBasell Industries Holdings, B.V. 2012

LyondellBasell markets this product through the following entities:

- ┆ Equistar Chemicals, LP
- ┆ Basell Sales & Marketing Company B.V.
- ┆ Basell Asia Pacific Limited
- ┆ Basell International Trading FZE
- ┆ LyondellBasell Australia Pty Ltd

For the contact details of the LyondellBasell company selling this product in your country, please visit <http://www.lyondellbasell.com/>.

Before using a product sold by a company of the LyondellBasell family of companies, users should make their own independent determination that the product is suitable for the intended use and can be used safely and legally. SELLER MAKES NO WARRANTY; EXPRESS OR IMPLIED (INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE OR ANY WARRANTY) OTHER THAN AS SEPARATELY AGREED TO BY THE PARTIES IN A CONTRACT.

This product(s) may not be used in:

- (i) any U.S. FDA Class I, Health Canada Class I, and/or European Union Class I medical devices, without prior notification to Seller for each specific product and application; or
 - (ii) the manufacture of any of the following, without prior written approval by Seller for each specific product and application: U.S. FDA Class II medical devices; Health Canada Class II or III medical devices; European Union Class II medical devices; or any equivalent U.S. FDA, Health Canada, or European Union regulations pertaining to medical devices; packaging in direct contact with a pharmaceutical active ingredient and/or dosage form; and tobacco-related products and applications.
- This product(s) may not be used in the manufacture of any of the following applications: U.S. FDA Class III medical devices; Health Canada Class IV medical devices; European Class III medical devices; applications involving permanent implantation into the body; life-sustaining medical applications; and lead, asbestos or MTBE related applications. All references to the U.S. FDA, Health Canada and European Union regulations include another country's equivalent regulatory classification.

Users should review the applicable Material Safety Data Sheet before handling the product.

Addhere, Adflex, Adstif, Adsyl, Akoafloor, Akoalit, Alathon, Alkylate, Amazing Chemistry, Aquamarine, Aquathene, Arconate, Arcopure, Arcosolv, Arctic Plus, Arctic Shield, Avant, Catalloy, Clyrell, CRP, Crystex, Dextflex, Duopac, Duoprime, Explore & Experiment, Filmex, Flexathene, Glacido, Hifax, Histif, Hostacom, Hostalen, Ideal, Integrate, Koattro, LIPP, Lucalen, Luflexen, Lupolen, Lupolex, Luposim, Lupostress, Lupotech, Metocene, Microthene, Moplen, MPDIOL, Nerolex, Nexprene, Petrothene, Plexar, Polymeg, Pristene, Prodflex, Pro-Fax, Punctilious, Purell, SAA100, SAA101, Sequel, Softell, Spherilene, Spheripol, Spherizone, Starflex, Stretchene, Superflex, TBAC , Tebol, T-Hydro, Toppyl, Trans4m, Tufflo, Ultrathene, Vacido and Valtec are trademarks owned or used by the LyondellBasell family of companies.

Adsyl, Akoafloor, Akoalit, Alathon, Aquamarine, Arconate, Arcopure, Arcosolv, Arctic Plus, Arctic Shield, Avant, CRP, Crystex, Dextflex, Duopac, Duoprime, Explore & Experiment, Filmex, Flexathene,

Hifax, Hostacom, Hostalen, Ideal, Integrate, Koattro, Lucalen, Lupolen, Microthene, Moplen, MPDIOL, Nexprene, Petrothene, Plexar, Polymeg, Pristene, Pro-Fax, Punctilious, Purell, Sequel, Softell, Spheripol, Spherizone, Starflex, Tebol, T-Hydro, Toppyl, Tufflo and Ultrathene are registered in the U.S. Patent and Trademark Office.

Release Date: 02 Feb 2004

