



Hostacom BB77G

Compounded Polyolefin

Product Description

Hostacom BB77G high melt flow, 2,000 MPa flexural modulus, UV-stabilized, 15% talc-filled polypropylene copolymer has an excellent balance of properties. Designed for automotive interior trim applications, this material colors easily, processes very well and provides parts with outstanding surface appearance.

Product Characteristics

Status	Commercial: Active
Test Method used	ISO
Availability	North America
Processing Methods	Injection Molding
Features	Pleasing Surface Appearance, Good Colorability, Copolymer, Good Dimensional Stability, High Flow , Good Moldability , High Rigidity , Good Weather Resistance

Typical Customer Applications Automotive Parts

Typical Properties	Method	Value	Unit
Physical			
Density	ISO 1183	1.00	g/cm ³
Melt flow rate (MFR) (230°C/2.16Kg)	ISO 1133	27	g/10 min
<i>Note: Alternative test method is ASTM D 1238-01.</i>			
Mechanical			
Tensile Stress at Yield	ISO 527-1, -2	26	MPa
Tensile Strain at Yield	ISO 527-1, -2	5	%
Flexural modulus	ISO 178	2000	MPa
Impact			
Notched izod impact strength	ISO 180		
(23 °C)		4.0	kJ/m ²
(-40 °C)		1.8	kJ/m ²
Thermal			
Heat deflection temperature B (0.45 MPa) Unannealed	ISO 75B-1, -2	110	°C
Heat deflection temperature A (1.80 MPa) Unannealed	ISO 75A-1, -2	60	°C
CLTE, Flow	ISO 11359-1, -2	5.3 x 10 ⁻⁵	cm/cm/°C
<i>Note: Determined over a temperature range of -30°C to 100°C. Alternative test method is ASTM E 228-95.</i>			
Additional Information			
Mold shrinkage	ISO 294-4		
<i>Note: Please contact Basell for shrinkage recommendations.</i>			

Notes

Typical properties; not to be construed as specifications.

© LyondellBasell Industries Holdings, B.V. 2014

LyondellBasell markets this product through the following entities:

- Equistar Chemicals, LP
- Basell Sales & Marketing Company B.V.
- Basell Asia Pacific Limited
- Basell International Trading FZE
- LyondellBasell Australia Pty Ltd

For the contact details of the LyondellBasell company selling this product in your country, please visit <http://www.lyb.com/>.

Before using a product sold by a company of the LyondellBasell family of companies, users should make their own independent determination that the product is suitable for the intended use and can be used safely and legally.

SELLER MAKES NO WARRANTY; EXPRESS OR IMPLIED (INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE OR ANY WARRANTY) OTHER THAN AS SEPARATELY AGREED TO BY THE PARTIES IN A CONTRACT.

This product(s) may not be used in:

(i) any U.S. FDA Class I, Health Canada Class I, and/or European Union Class I Medical Devices, without prior notification to Seller for each specific product and application; or

(ii) the manufacture of any of the following, without prior written approval by Seller for each specific product and application: (1) U.S. FDA Class II, Health Canada Class II or Class III, and/or European Union Class II Medical Devices; (2) film, overwrap and/or product packaging that is considered a part or component of one of the aforementioned Medical Devices; (3) packaging in direct contact with a pharmaceutical active ingredient and/or dosage form that is intended for inhalation, injection, intravenous, nasal, ophthalmic (eye), digestive, or topical (skin) administration; (4) tobacco related products and applications; (5) electronic cigarettes and similar devices; and (6) pressure pipe or fittings that are considered a part or component of a nuclear reactor.

(iii) Additionally, the product(s) may not be used in: (1) U.S. FDA Class III, Health Canada Class IV, and/or European Class III Medical Devices; (2) applications involving permanent implantation into the body; (3) life-sustaining medical applications; and (4) lead, asbestos or MTBE related applications.

All references to U.S. FDA, Health Canada, and European Union regulations include another country's equivalent regulatory classification.

Users should review the applicable Material Safety Data Sheet before handling the product.

Addhere, Adflex, Adstif, Adsyl, Akoafloor, Akoalit, Alastian, Alathon, Alkylate, Amazing Chemistry, Aquamarine, Aquathene, Arctic Plus, Arctic Shield, Avant, Catalloy, Clyrell, CRP, Crystex, Dexflex, Duopac, Duoprime, Explore & Experiment, Filmex, Flexathene, Fueling the power to win, Get in touch with, Glacido, Hifax, Histif, Hostacom, Hostalen PP, Hostalen ACP, Ideal, Indure, Integrate, Koattro, LIPP, Lucalen, Luflexen, Lupolen, Lupolex, Luposim, Lupostress, Lupotech, Metocene, Microthene, Moplen, MPDIOL, Nerolex, Nexprene, Petrothene, Plexar, Polymeg, Pristene, Prodflex, Pro-fax, Punctilious, Purell, Refax, SAA100, SAA101, Sequel, Softell, Spherilene, Spheripol, Spherizone, Starflex, Stretchene, Superflex, TBAC, Tebol, T-Hydro, Toppyl, Trans4m, Tufflo, Ultrathene, Vacido and Valtec, are trademarks owned and/or used by the LyondellBasell family of companies.

Adsyl, Akoafloor, Akoalit, Alastian, Alathon, Aquamarine, Arctic Plus, Arctic Shield, Avant, CRP, Crystex, Dexflex, Duopac, Duoprime, Explore & Experiment, Filmex, Flexathene, Hifax, Hostacom, Hostalen, Ideal, Integrate, Koattro, Lucalen, Lupolen, Metocene, Microthene, Moplen, MPDIOL, Nexprene, Petrothene, Plexar, Polymeg, Pristene, Pro-fax, Punctilious, Purell, Sequel, Softell, Spheripol, Spherizone, Starflex, Tebol, T-Hydro, Toppyl, Tufflo, Ultrathene are registered in the U.S. Patent and Trademark Office.

Release Date: 31 Oct 2007