



Hostacom CB271FC

Compounded Polyolefin

Product Description

Hostacom CB271FC high melt flow, 2,000 MPa flexural modulus, precolored, UV-stabilized, mineral-filled thermoplastic elastomeric olefin (TEO) resin has an excellent combination of stiffness, impact resistance and processability. It was designed primarily for automotive interior applications that demand balanced performance characteristics, such as those that require compliance to FMVSS201 or FMVSS208.

The Hostacom CB271 product family also includes CB271PC (UV-stabilized, paintable). Please discuss the application requirements with your Basell representative before selecting a specific grade.

Product Characteristics

Status	Commercial: Active
Test Method used	ISO
Availability	North America
Processing Method	Injection Molding
Features	Good Dimensional Stability, High Flow , Good Impact Resistance , Good Moldability , High Rigidity , Good UV Resistance
Typical Customer Applications	Interior Applications, Instrument Panels

Typical Properties	Method	Value Unit
Physical		
Density	ISO 1183	1.04 g/cm ³
Melt flow rate (MFR) (230°C/2.16Kg)	ISO 1133	20 g/10 min
Note: Alternative test method is ASTM D 1238-01.		
Mechanical		
Tensile Stress at Yield	ISO 527-1, -2	25 MPa
Tensile Strain at Yield	ISO 527-1, -2	11 %
Flexural modulus	ISO 178	2000 MPa
Impact		
Notched izod impact strength	ISO 180	
(23 °C)		24 kJ/m ²
(-30 °C)		3.3 kJ/m ²
Thermal		
Heat deflection temperature B (0.45 MPa)	ISO 75B-1, -2	108 °C
Unannealed		
Heat deflection temperature A (1.80 MPa)	ISO 75A-1, -2	62 °C
Unannealed		
CLTE, Flow	ISO 11359-1, -2	4.5 x 10 ⁻⁵ cm/cm/°C
Note: Determined over a temperature range of -30°C to 100°C. Alternative test method is ASTM E 228-95.		
Additional Information		
Mold shrinkage	ISO 294-4	
Note: Please contact Basell for shrinkage recommendations.		

Notes

Typical properties; not to be construed as specifications.

© LyondellBasell Industries Holdings, B.V. 2012

LyondellBasell markets this product through the following entities:

- ┆ Equistar Chemicals, LP
- ┆ Basell Sales & Marketing Company B.V.
- ┆ Basell Asia Pacific Limited
- ┆ Basell International Trading FZE
- ┆ LyondellBasell Australia Pty Ltd

For the contact details of the LyondellBasell company selling this product in your country, please visit <http://www.lyondellbasell.com/>.

Before using a product sold by a company of the LyondellBasell family of companies, users should make their own independent determination that the product is suitable for the intended use and can be used safely and legally. SELLER MAKES NO WARRANTY; EXPRESS OR IMPLIED (INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE OR ANY WARRANTY) OTHER THAN AS SEPARATELY AGREED TO BY THE PARTIES IN A CONTRACT.

This product(s) may not be used in:

- (i) any U.S. FDA Class I, Health Canada Class I, and/or European Union Class I medical devices, without prior notification to Seller for each specific product and application; or

(ii) the manufacture of any of the following, without prior written approval by Seller for each specific product and application: U.S. FDA Class II medical devices; Health Canada Class II or III medical devices; European Union Class II medical devices; or any equivalent U.S. FDA, Health Canada, or European Union regulations pertaining to medical devices; packaging in direct contact with a pharmaceutical active ingredient and/or dosage form; and tobacco-related products and applications. This product(s) may not be used in the manufacture of any of the following applications: U.S. FDA Class III medical devices; Health Canada Class IV medical devices; European Class III medical devices; applications involving permanent implantation into the body; life-sustaining medical applications; and lead, asbestos or MTBE related applications. All references to the U.S. FDA, Health Canada and European Union regulations include another country's equivalent regulatory classification.

Users should review the applicable Material Safety Data Sheet before handling the product.

Addhere, Adflex, Adstif, Adsyl, Akoafloor, Akoalit, Alathon, Alkylate, Amazing Chemistry, Aquamarine, Aquathene, Arconate, Arcopure, Arcosolv, Arctic Plus, Arctic Shield, Avant, Catalloy, Clyrell, CRP, Crystex, Dexflex, Duopac, Duoprime, Explore & Experiment, Filmex, Flexathene, Glacido, Hifax, Histif, Hostacom, Hostalen, Ideal, Integrate, Koattro, LIPP, Lucalen, Luflexen, Lupolen, Lupolex, Luposim, Lupostress, Lupotech, Metocene, Microthene, Moplen, MPDIOL, Nerolex, Nexprene, Petrothene, Plexar, Polymeg, Pristene, Pro-Fax, Punctilious, Purell, SAA100, SAA101, Sequel, Softell, Spherilene, Spheripol, Spherizone, Starflex, Stretchene, Superflex, TBAC, Tebol, T-Hydro, Toppyl, Trans4m, Tufflo, Ultrathene, Vacido and Valtec are trademarks owned or used by the LyondellBasell family of companies.

Adsyl, Akoafloor, Akoalit, Alathon, Aquamarine, Arconate, Arcopure, Arcosolv, Arctic Plus, Arctic Shield, Avant, CRP, Crystex, Dexflex, Duopac, Duoprime, Explore & Experiment, Filmex, Flexathene, Hifax, Hostacom, Hostalen, Ideal, Integrate, Koattro, Lucalen, Lupolen, Microthene, Moplen, MPDIOL, Nexprene, Petrothene, Plexar, Polymeg, Pristene, Pro-Fax, Punctilious, Purell, Sequel, Softell, Spheripol, Spherizone, Starflex, Tebol, T-Hydro, Toppyl, Tufflo and Ultrathene are registered in the U.S. Patent and Trademark Office.

Release Date: 06 Dec 2007