

Technical Data Sheet

**Hostacom PPH GF 30 LW LE H3 BLACK**

Polypropylene Homopolymer
LyondellBasell Industries
Engineering Plastics

Product Description

30% glass fibre reinforced PP-Homopolymer, long term heat stabilized, laser weldable, low emission. Available in black color.

General

Material Status	• Commercial: Active		
Availability	• Europe		
Features	• Heat Stabilized • Homopolymer	• Laser Weldable • Low Emissions	
Processing Method	• Injection Molding		

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density	1.11 g/cm ³	1.11 g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	5.1 g/10 min	5.1 g/10 min	ISO 1133
Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Modulus	928000 psi	6400 MPa	ISO 527-1
Tensile Stress (Break)	11600 psi	80.0 MPa	ISO 527-2
Tensile Strain (Break)	3.5 %	3.5 %	ISO 527-2
Flexural Modulus	899000 psi	6200 MPa	ISO 178
Flexural Stress (3.5% Strain)	18300 psi	126 MPa	ISO 178
Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Charpy Notched Impact Strength (73°F (23°C))	4.4 ft·lb/in ²	9.2 kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength 73°F (23°C)	25 ft·lb/in ²	52 kJ/m ²	ISO 179/1eU
Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Deflection Temperature Under Load 66 psi (0.45 MPa), Unannealed	313 °F	156 °C	ISO 75-2/B
264 psi (1.8 MPa), Unannealed	266 °F	130 °C	ISO 75-2/Af
Flammability	Nominal Value (English)	Nominal Value (SI)	Test Method
Burning Rate (0.0787 in (2.00 mm))	< 3.9 in/min	< 100 mm/min	FMVSS 302
Flame Rating			UL 94
0.06 in (1.5 mm)	HB	HB	
0.12 in (3.0 mm)	HB	HB	

Technical Data Sheet



Hostacom PPH GF 30 LW LE H3 BLACK

Polypropylene Homopolymer
LyondellBasell Industries
Engineering Plastics



Injection	Nominal Value (English)	Nominal Value (SI)
Drying Temperature	176 °F	80 °C
Drying Time	2.0 to 3.0 hr	2.0 to 3.0 hr
Processing (Melt) Temp	428 to 500 °F	220 to 260 °C
Mold Temperature	86 to 140 °F	30 to 60 °C

Injection Notes

Drying normally not necessary.

Injection molding parameters also influence emission properties, which are often required for automotive interior applications. Generally speaking, the emission, odor and fogging behavior of finished parts is improved by lowering the melt temperature, reducing residence time and avoiding high shear stress.

Notes

These are typical property values not to be construed as specification limits.

Processing Techniques

Specific recommendations for resin type and processing conditions can only be made when the end use, required properties and fabrication equipment are known.

Product Storage and Handling

- Product should be stored in dry conditions at temperatures below 50°C and protected from UV-light
- Improper storage may bring damage to the packaging and can negatively affects on the quality of this product
- Keep material completely dry for good processing

Company Information

For further information regarding the LyondellBasell company, please visit <http://www.lyb.com/>.

© LyondellBasell Industries Holdings, B.V. 2024

Disclaimer

Information in this document is accurate to the best of our knowledge at the date of publication. The document is designed to provide users general information for safe handling, use, processing, storage, transportation, disposal and release and does not constitute any warranty or quality specification, either express or implied, including any warranty of merchantability or fitness for any particular purpose. Users shall determine whether the product is suitable for their use and can be used safely and legally.

In addition to any prohibitions of use specifically noted in this document, LyondellBasell may further prohibit or restrict the sale of its products into certain applications. For further information, please contact a LyondellBasell representative.

Trademarks

The Trademark referenced within the product name is owned or used by the LyondellBasell family of companies.