

Basell - Hostacom SP 98/E/96 - Compounded Polyolefin



Hostacom SP 98/E/96

Compounded Polyolefin

Product Description

"Hostacom" SP 98/E 96 is a low melt flow, 30% mineral filled , high UV stabilised polypropylene copolymer. It is mainly designed for extrusion applications. The grade is available in black and custom colour, in pellet form.

Product Characteristics

Status	Commercial: Active
Test Method used	ISO
Availability	Europe, North America, Latin America
Features	Copolymer, Flow, Low, Toxicity, None
Typical Customer Applications	Automotive Parts

Typical Properties	Method	Value	Unit
Physical			
Density (Method A)	ISO 1183	1.20	g/cm ³
Melt flow rate (MFR) (230°C/2.16Kg)	ISO 1133	0.7	g/10 min
Mechanical			
Flexural modulus	ISO 178	2100	MPa
Impact			
Notched izod impact strength (-20 °C, Type 1, Notch A)	ISO 180	4.5	kJ/m ²

Notes

Typical properties; not to be construed as specifications.

© 2003 Basell Service Company B.V.

For the contact details of the LyondellBasell company selling this product in your country, please visit <http://www.basell.com/>.

Before using a LyondellBasell product, customers and other users should make their own independent determination that the product is suitable for the intended use. They should also ensure that they can use the LyondellBasell product safely and legally. This document does not constitute a warranty, express or implied, including a warranty of merchantability or fitness for a particular purpose. In addition, no immunity under LyondellBasell's or third parties' intellectual property rights shall be implied from this document. No one is authorized to make any warranties, issue any immunities or assume any liabilities on behalf of LyondellBasell except in a writing signed by an authorized LyondellBasell employee. Unless otherwise agreed in writing, the exclusive remedy for all claims is replacement of the product or refund of the purchase price at LyondellBasell's option, and in no event shall LyondellBasell be liable for special, consequential, incidental, punitive or exemplary damages.

CRP, Adflex, Adstif, Adsyl, Akoalit, Akoafloor, Avant, Catalloy, Clyrell, Entegrit, Get in touch with, Hifax, Higran, Histif, Hostacom, Hostalen, LIPP, Lucalen, Luflexen, Lupocomp, Lupolen, Lupolex, Luposim, Lupostress, Lupotech, Metocene, Moplen, Pristene, Purell, Pro-fax, Sholybox, Softell, Spherilene, Spheripol, Spherizone, Stretchene, Toppyl and Valtec are trademarks owned or used by LyondellBasell group companies.

Basell - Hostacom SP 98/E/96 - Compounded Polyolefin

Adflex, Adstif, Adsyl, Clyrell, CRP, Hifax, Hostacom, Hostalen, Lucalen, Luflexen, Lupolen, Lupotech, Moplen and Pro-fax are registered in the U.S. Patent and Trademark Office.

Unless specifically indicated, the grades mentioned are not suitable for applications in the pharmaceutical/medical sector.

Release Date: 19 Feb 2004