



Hostacom TRC 352NA

Compounded Polyolefin

Product Description

Hostacom TRC 352NA high melt flow, high flexural modulus, mineral-filled thermoplastic elastomeric olefin (TEO) resin has excellent impact/stiffness balance, good flowability properties, and excellent scratch resistance. It has an outstanding blooming resistance at elevated temperatures. It was designed primarily for interior automotive applications.

Product Characteristics

Status	Commercial: Active
Test Method used	ISO
Availability	North America
Processing Method	Injection Molding
Features	Good Flow, Scratch Resistant, Impact Modified
Typical Customer Applications	Interior Applications

Typical Properties	Method	Value Unit
Physical		
Melt flow rate	ASTM D 1238	18 g/10 min
Density	ISO 1183	1.05 g/cm ³
Mechanical		
Tensile Stress at Yield (23 °C, 50 mm/min)	ISO 527-1, -2	20 MPa
Flexural modulus (23 °C, 2 mm/min)	ISO 178	1850 MPa
<i>Note: Modulus Type - Chord</i>		
Impact		
Charpy unnotched impact strength (23 °C, Type 1, Edgewise)	ISO 179	No Break kJ/m ²
Charpy notched impact strength (23 °C, Type 1, Edgewise, Notch A)	ISO 179	35 kJ/m ²
(-30 °C, Type 1, Edgewise, Notch A)		4.5 kJ/m ²
Additional Information		
Mold shrinkage	ISO 294-4	
<i>Note: Please contact LyondellBasell for shrinkage recommendations.</i>		

Notes

Typical properties; not to be construed as specifications.

© LyondellBasell Industries Holdings, B.V. 2011

LyondellBasell markets this product through the following entities:

Equistar Chemicals, LP
 Basell Sales & Marketing Company B.V.
 Basell Asia Pacific Limited
 Basell International Trading FZE
 LyondellBasell Australia Pty Ltd

For the contact details of the LyondellBasell company selling this product in your country, please visit <http://www.lyondellbasell.com/>.

Before using a product sold by one of the LyondellBasell family of companies, users should make their own independent determination that the product is suitable for the intended use and can be used safely and legally. SELLER MAKES NO WARRANTY; EXPRESS OR IMPLIED (INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE) OTHER THAN AS SEPARATELY AGREED BETWEEN THE PARTIES IN WRITING. This product(s) may not be used in the manufacture of any US FDA Class III Medical Device or Health Canada Class IV Medical Device and may not be used in the manufacture of any US FDA Class II Medical Device or Health Canada Class II or Class III Medical Device without the prior written approval by Seller of each specific product or application.

Users should review the applicable Material Safety Data Sheet before handling the product.

Adflex, Adstif, Adsyl, Akoafloor, Akoalit, Alastian, Alathon, Alkylate, Amazing Chemistry, Aquamarine, Aquathene, Arconate, Arcopure, Arcosolv, Arctic Plus, Arctic Shield, Avant, Catalloy, Clyrell, CRP, Crystex, Dextflex, Duopac, Duoprime, Explore & Experiment, Filmex, Flexathene, Fueling the Power to Win, Get in touch with, Glacido, Hifax, Histif, Hostacom, Hostalen, Ideal, Integrate, Koattro, LIPP, Lucalen, Luflexen, Lupolen, Lupolex, Luposim, Lupostress, Lupotech, Metocene, Microthene, Moplen, MPDIOL, Nerolex, Nexprene, Petrothene, Plexar, Polymeg, Pristene, Prodflex, Pro-Fax, Punctilious, Purell, SAA100, SAA101, Sequel, Softell, Spherilene, Spheripol, Spherizone, Starflex, Stretchene, Superflex, TBAC, Tebol, T-Hydro, Toppyl, Trans4m, Tufflo, Ultrathene, Vacido and Valtec are trademarks owned or used by the LyondellBasell family of companies.

Adsyl, Akoafloor, Akoalit, Alastian, Alathon, Aquamarine, Arconate, Arcopure, Arcosolv, Arctic Plus, Arctic Shield, Avant, Clyrell, CRP, Crystex, Dextflex, Duopac, Duoprime, Explore & Experiment, Filmex, Flexathene, Hifax, Hostacom, Hostalen, Ideal, Integrate, Koattro, Lucalen, Lupolen, Microthene, Moplen, MPDIOL, Nexprene, Petrothene, Plexar, Polymeg, Pristene, Pro-Fax, Punctilious, Purell, Sequel, Softell, Spheripol, Spherizone, Starflex, Tebol, T-Hydro, Toppyl, Tufflo and Ultrathene are registered in the U.S. Patent and Trademark Office.

Release Date: 22 Nov 2010

