



Hostacom TRC 364NA

Compounded Polyolefin

Product Description

Hostacom TRC 364NA high melt flow, high modulus, mineral-filled thermoplastic elastomeric olefin (TEO) resin was designed for interior trim applications and displays exceptional scratch and mar resistance, low stress whitening, and low emissions.

Product Characteristics

Status	Commercial: Active
Test Method used	ISO
Availability	North America
Processing Method	Injection Molding
Features	High Flow , Good Impact Resistance , Scratch Resistant, Good Stiffness , Good UV Resistance

Typical Properties	Method	Value Unit
Physical		
Density	ISO 1183	1.03 g/cm ³
Melt flow rate (MFR)	ISO 1133	17 g/10 min
Mechanical		
Tensile Stress at Yield (50 mm/min)	ISO 527-1, -2	21 MPa
Tensile Strain at Yield (50 mm/min)	ISO 527-1, -2	7 %
Flexural modulus (2 mm/min, Chord)	ISO 178	1800 MPa
Impact		
Charpy notched impact strength (23 °C, Type 1, Edgewise, Notch A)	ISO 179	40 kJ/m ²

Notes

Typical properties; not to be construed as specifications.

© LyondellBasell Industries Holdings, B.V. 2011
LyondellBasell markets this product through the following entities: Equistar Chemicals, LP Basell Sales & Marketing Company B.V. Basell Asia Pacific Limited Basell International Trading FZE LyondellBasell Australia Pty Ltd
For the contact details of the LyondellBasell company selling this product in your country, please visit http://www.lyondellbasell.com/ .
Before using a product sold by one of the LyondellBasell family of companies, users should make their own independent determination that the product is suitable for the intended use and can be used safely and legally. SELLER MAKES NO WARRANTY; EXPRESS OR IMPLIED (INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE) OTHER THAN AS SEPARATELY AGREED BETWEEN THE PARTIES IN WRITING. This product(s) may not be used in the manufacture of any US FDA Class III Medical Device or Health Canada Class IV Medical Device and may not be used in the manufacture of any US FDA Class II Medical Device or Health Canada Class II or Class III Medical Device without the prior written approval by Seller of each specific product or application.
Users should review the applicable Material Safety Data Sheet before handling the product.
<i>Adflex, Adstif, Adsyl, Akoafloor, Akoalit, Alastian, Alathon, Alkylate, Amazing Chemistry, Aquamarine, Aquathene, Arconate, Arcopure, Arcosolv, Arctic Plus, Arctic Shield, Avant, Catalloy, Clyrell, CRP, Crystex, Dexflex, Duopac, Duoprime, Explore & Experiment, Filmex, Flexathene, Fueling the Power to Win, Get in touch with, Glacido, Hifax, Histif, Hostacom, Hostalen, Ideal, Integrate, Koattro, LIPP, Lucalen, Lufflexen, Lupolen, Lupolex, Luposim, Lupostress, Lupotech, Metocene, Microthene, Moplen, MPDIOL, Nerolex, Nexprene, Petrothene, Plexar, Polymeg, Pristene, Proddflex, Pro-Fax, Punctilious, Purell, SAA100, SAA101, Sequel, Softell, Spherilene, Spheripol, Spherizone, Starflex, Stretchene, Superflex, TBAC, Tebol, T-Hydro, Toppyl, Trans4m, Tufflo, Ultrathene, Vacido and Valtec</i> are trademarks owned or used by the LyondellBasell family of companies.
<i>Adsyl, Akoafloor, Akoalit, Alastian, Alathon, Aquamarine, Arconate, Arcopure, Arcosolv, Arctic Plus, Arctic Shield, Avant, Clyrell, CRP, Crystex, Dexflex, Duopac, Duoprime, Explore & Experiment, Filmex, Flexathene, Hifax, Hostacom, Hostalen, Ideal, Integrate, Koattro, Lucalen, Lupolen, Microthene, Moplen, MPDIOL, Nexprene, Petrothene, Plexar, Polymeg, Pristene, Pro-Fax, Punctilious, Purell, Sequel, Softell, Spheripol, Spherizone, Starflex, Tebol, T-Hydro, Toppyl, Tufflo and Ultrathene</i> are registered in the U.S. Patent and Trademark Office.
Release Date: 04 Feb 2011