

[Home](#) / [Products & Technology](#) / [Polymers](#) / **Hostacom TRC104N/1 NATRL**

Hostacom TRC104N/1 NATRL

Description

Hostacom TRC 104N/1 NATRL high melt flow, >1,750 MPa flexural modulus, mineral-filled thermoplastic elastomeric olefin (TEO) resin has an excellent balance of properties and processability. It is typically used for automotive instrument panels and other interior applications.

Availability

North America

[» CustomerXpress](#)[» Find a Sales Contact](#)[» Request Product Information](#)

Legend

SDS - Safety Data Sheet

PSB - Product Stewardship Bulletin

[Information](#)[SDS](#)[PSB](#)[Safety Summary](#)

Product Data and Technical Information

Typical Properties

Melt Flow Rate (230°C/2.16 kg)	22 g/10 min
Density (23°C)	1.04 g/cm ³
Flexural Modulus (23°C)	>1750 MPa
Flexural Stress (23°C)	28.0 MPa
Tensile Stress at Yield (23°C)	19.5 MPa
Tensile Strain at Break (23°C)	>80 %
Notched Izod Impact Strength (23°C)	>20 kJ/m ²
Notched Izod Impact Strength (-30°C)	>2.0 kJ/m ²
Rockwell Hardness	>60
Deflection Temperature Under Load (0.45 MPa, Unannealed)	106 °C
Mold Shrinkage	

Process

Injection Molding

Resin

Polypropylene Compounds

Applications

Instrument Panels, Interior Automotive Applications

Prohibited Applications of Compounded Polyolefins:

The use of LyondellBasell Compounded Polyolefins in the following applications is prohibited:

- All parts for Aeronautical use
- All parts for Train transportation use
- Air bag unit housings
- Seat belt systems and mechanisms
- Brake systems and mechanisms
- Pedals (brake, gas, clutch)
- Steering systems and mechanisms
- All parts with flammability requirements for Building and Constructions
- All parts with flammability requirements for Industrial applications use
- All parts for Medical applications use

This site uses cookies. By continuing to browse the site, you agree to our use of cookies.

» ACCEPT

[Privacy](#)