

Technical Data Sheet

**Icorene - Semi Conductives 1761 SC Black 9002**

Metallocene Medium Density Polyethylene
LyondellBasell Industries
Rotomolding

Product Description

ICORENE® 1761SC Black 9002 is a special electrically conductive black medium density metallocene polyethylene powder designed for rotational moulding applications.

It is suitable for use in applications where permanent semi conductive or antistatic behaviour is required. It has a good balance of properties such as toughness, easy flow, reasonable impact, and surface gloss.

General

Material Status	• Commercial: Active
Availability	• Europe
Additive	• UV Stabilizer
Features	• Good Toughness • Semi Conductive • UV Resistant
Uses	• General Purpose
Appearance	• Black
Forms	• Powder
Processing Method	• Rotational Molding

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density	0.934 g/cm ³	0.934 g/cm ³	ASTM D1505
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	6.0 g/10 min	6.0 g/10 min	ASTM D1238
Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Strength (Yield)	2180 psi	15.0 MPa	ASTM D638
Flexural Modulus	87000 psi	600 MPa	ASTM D790
Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Vicat Softening Temperature	250 °F	121 °C	ISO 306
Melting Temperature	253 °F	123 °C	ISO 11357
Electrical	Nominal Value (English)	Nominal Value (SI)	Test Method
Surface Resistivity	1.0E+5 ohms	1.0E+5 ohms	IEC 61340-2-3

Notes

These are typical property values not to be construed as specification limits.

Processing Techniques

Specific recommendations for resin type and processing conditions can only be made when the end use, required properties and fabrication equipment are known.

Product Storage and Handling

- Product should be stored in dry conditions at temperatures below 50°C and protected from UV-light
- Improper storage may bring damage to the packaging and can negatively affects on the quality of this product
- Keep material completely dry for good processing

Company Information

For further information regarding the LyondellBasell company, please visit <http://www.lyb.com/>.

© LyondellBasell Industries Holdings, B.V. 2024

Disclaimer

Information in this document is accurate to the best of our knowledge at the date of publication. The document is designed to provide users general information for safe handling, use, processing, storage, transportation, disposal and release and does not constitute any warranty or quality specification, either express or implied, including any warranty of merchantability or fitness for any particular purpose. Users shall determine whether the product is suitable for their use and can be used safely and legally.

In addition to any prohibitions of use specifically noted in this document, LyondellBasell may further prohibit or restrict the sale of its products into certain applications. For further information, please contact a LyondellBasell representative.

Trademarks

Technical Data Sheet

**Icorene - Semi Conductives 1761 SC Black 9002**

Metallocene Medium Density Polyethylene
LyondellBasell Industries
Rotomolding

The Trademark referenced within the product name is owned or used by the LyondellBasell family of companies.