

Technical Data Sheet



Icorene 1613

Linear Medium Density Polyethylene
LyondellBasell Industries
Rotomolding

Product Description

ICORENE® 1613 is a hexene linear medium density polyethylene specifically developed for use in rotational moulding.

This grade is designed for applications requiring good processability, stiffness and toughness. The constituents of this product are suitable for food contact applications.

ICORENE® 1613 is TÜV approved, protocolnr 175XS0124-00.

General

Material Status	• Commercial: Active		
Availability	• Europe		
Additive	• UV Stabilizer		
Features	• Food Contact Acceptable • Good Impact Resistance • Good Processability	• Good Stiffness • Good Toughness • Hexene Comonomer	• UV Resistant
Uses	• Tanks		
Appearance	• Natural Color	• Unspecified Color	
Forms	• Powder		
Processing Method	• Rotational Molding		

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density (73°F (23°C))	0.938 g/cm³	0.938 g/cm³	ISO 1183
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	4.5 g/10 min	4.5 g/10 min	ISO 1133
Environmental Stress-Cracking Resistance (ESCR)			ASTM D1693B
122°F (50°C), 10% Igepal, F50	> 250 hr	> 250 hr	
122°F (50°C), 100% Igepal, F50	> 1000 hr	> 1000 hr	
Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Strength			ISO 527-1
Yield, 73°F (23°C), 0.126 in (3.20 mm), Rotational Molded	2900 psi	20.0 MPa	
Tensile Elongation			ISO 527-1
Break, Rotational Molded	> 1000 %	> 1000 %	
Flexural Modulus (73°F (23°C))	109000 psi	750 MPa	ISO 178
Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Drop Impact Resistance ¹ (-4°F (-20°C))	> 4.50 in-lb/mil	> 200 J/cm	Internal Method
Hardness	Nominal Value (English)	Nominal Value (SI)	Test Method
Shore Hardness (Shore D)	62	62	ISO 868
Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Deflection Temperature Under Load			ISO 75-2/B
66 psi (0.45 MPa), Unannealed	149 °F	65.0 °C	
Vicat Softening Temperature	243 °F	117 °C	ISO 306/A
Melting Temperature	261 °F	127 °C	ISO 11357-3

Notes

¹ based on ISO 6603

Notes

These are typical property values not to be construed as specification limits.

Processing Techniques

Specific recommendations for resin type and processing conditions can only be made when the end use, required properties and fabrication equipment are known.

Product Storage and Handling

Technical Data Sheet



Icorene 1613

Linear Medium Density Polyethylene
LyondellBasell Industries
Rotomolding

- Product should be stored in dry conditions at temperatures below 50°C and protected from UV-light
- Improper storage may bring damage to the packaging and can negatively affects on the quality of this product
- Keep material completely dry for good processing

Company Information

For further information regarding the LyondellBasell company, please visit <http://www.lyb.com/>.

© LyondellBasell Industries Holdings, B.V. 2024

Disclaimer

Information in this document is accurate to the best of our knowledge at the date of publication. The document is designed to provide users general information for safe handling, use, processing, storage, transportation, disposal and release and does not constitute any warranty or quality specification, either express or implied, including any warranty of merchantability or fitness for any particular purpose. Users shall determine whether the product is suitable for their use and can be used safely and legally.

In addition to any prohibitions of use specifically noted in this document, LyondellBasell may further prohibit or restrict the sale of its products into certain applications. For further information, please contact a LyondellBasell representative.

Trademarks

The Trademark referenced within the product name is owned or used by the LyondellBasell family of companies.