

Technical Data Sheet

**Icorene 1761 Black 9001**

Metallocene Linear Low Density Polyethylene
LyondellBasell Industries
Rotomolding

Product Description

ICORENE® 1761 BLACK 9001 is a metallocene linear low density polyethylene for rotational moulding applications.

This grade is specifically developed for dieseltanks. It has a good balance of properties such as toughness, easy flow and high impact.

General

Material Status	• Commercial: Active		
Availability	• Europe		
Additive	• UV Stabilizer		
Features	• Good Toughness • High Flow	• High Gloss • High Impact Resistance	• UV Resistant
Uses	• General Purpose	• Tanks	
Appearance	• Black		
Forms	• Powder		
Processing Method	• Rotational Molding		

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density	0.935 g/cm ³	0.935 g/cm ³	ASTM D1505
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	6.0 g/10 min	6.0 g/10 min	ASTM D1238
Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Strength			ISO 527-2
Yield	2610 psi	18.0 MPa	
Break	2760 psi	19.0 MPa	
Tensile Elongation (Break)	> 700 %	> 700 %	ISO 527-2
Flexural Modulus	102000 psi	700 MPa	ISO 178
Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Drop Impact Resistance ¹ (-4°F (-20°C))	4.27 in-lb/mil	190 J/cm	Internal Method
Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Vicat Softening Temperature	250 °F	121 °C	ISO 306
Melting Temperature	253 °F	123 °C	ISO 11357

Notes

¹ Based on ISO 6603

Notes

These are typical property values not to be construed as specification limits.

Processing Techniques

Specific recommendations for resin type and processing conditions can only be made when the end use, required properties and fabrication equipment are known.

Product Storage and Handling

- Product should be stored in dry conditions at temperatures below 50°C and protected from UV-light
- Improper storage may bring damage to the packaging and can negatively affects on the quality of this product
- Keep material completely dry for good processing

Company Information

For further information regarding the LyondellBasell company, please visit <http://www.lyb.com/>.

© LyondellBasell Industries Holdings, B.V. 2024

Disclaimer

Information in this document is accurate to the best of our knowledge at the date of publication. The document is designed to provide users general information for safe handling, use, processing, storage, transportation, disposal and release and does not constitute any warranty or quality specification,

Technical Data Sheet

**Icorene 1761 Black 9001**

Metallocene Linear Low Density Polyethylene
LyondellBasell Industries
Rotomolding

either express or implied, including any warranty of merchantability or fitness for any particular purpose. Users shall determine whether the product is suitable for their use and can be used safely and legally.

In addition to any prohibitions of use specifically noted in this document, LyondellBasell may further prohibit or restrict the sale of its products into certain applications. For further information, please contact a LyondellBasell representative.

Trademarks

The Trademark referenced within the product name is owned or used by the LyondellBasell family of companies.