

Technical Data Sheet

**Icorene 2551**

Linear Low Density Polyethylene

LyondellBasell Industries

Rotomolding

Product Description

ICORENE® 2551 is a linear low density polyethylene powder specifically developed for rotational moulding.

This grade has been designed for applications requiring good processability, toughness and flexibility and is suitable in many different applications.

General

Material Status	• Commercial: Active		
Availability	• Europe		
Additive	• UV Stabilizer		
Features	• Good Flexibility • Good Processability	• Good Toughness • UV Resistant	
Uses	• Flotation Devices	• Furniture	• Outdoor Furnishings
Appearance	• Natural Color	• Unspecified Color	
Forms	• Powder		
Processing Method	• Rotational Molding		

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density	0.925 g/cm ³	0.925 g/cm ³	ASTM D1505
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	5.0 g/10 min	5.0 g/10 min	ASTM D1238
Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Strength (Yield)	1600 psi	11.0 MPa	ASTM D638
Flexural Modulus	47900 psi	330 MPa	ASTM D790
Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Drop Impact Resistance ¹ (-4°F (-20°C))	4.05 in·lb/mil	180 J/cm	Internal Method
Hardness	Nominal Value (English)	Nominal Value (SI)	Test Method
Durometer Hardness	50	50	ASTM D2240

Notes

¹ Based on ISO 6603

Notes

These are typical property values not to be construed as specification limits.

Processing Techniques

Specific recommendations for resin type and processing conditions can only be made when the end use, required properties and fabrication equipment are known.

Product Storage and Handling

- Product should be stored in dry conditions at temperatures below 50°C and protected from UV-light
- Improper storage may bring damage to the packaging and can negatively affects on the quality of this product
- Keep material completely dry for good processing

Company Information

For further information regarding the LyondellBasell company, please visit <http://www.lyb.com/>.

© LyondellBasell Industries Holdings, B.V. 2024

Disclaimer

Information in this document is accurate to the best of our knowledge at the date of publication. The document is designed to provide users general information for safe handling, use, processing, storage, transportation, disposal and release and does not constitute any warranty or quality specification, either express or implied, including any warranty of merchantability or fitness for any particular purpose. Users shall determine whether the product is suitable for their use and can be used safely and legally.

In addition to any prohibitions of use specifically noted in this document, LyondellBasell may further prohibit or restrict the sale of its products into certain applications. For further information, please contact a LyondellBasell representative.

Technical Data Sheet**Icorene 2551**

Linear Low Density Polyethylene
LyondellBasell Industries
Rotomolding

Trademarks

The Trademark referenced within the product name is owned or used by the LyondellBasell family of companies.