

Technical Data Sheet

**Icorene N1016**

Ethylene Vinyl Acetate Copolymer
LyondellBasell Industries
Custom Powders

Product Description

ICORENE® N1016 is a premium copolymer of ethylene vinyl acetate specifically designed for the preparation of masterbatch and textile bonding. The powder form can achieve better colour developments or additive dispersion in a masterbatch than the pellet form.

The vinyl acetate content is about 28%.

This grade can be used in various applications such as hot melt adhesives with a maximum processing temperature of 200°C.

General

Material Status	• Commercial: Active		
Availability	• Europe		
Additive	• Heat Stabilizer		
Features	• Copolymer • Dispersible	• Food Contact Acceptable • Good Colorability	• Heat Stabilized
Uses	• Adhesives	• Masterbatch	
Forms	• Powder		

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density	0.948 g/cm ³	0.948 g/cm ³	Internal Method
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	150 g/10 min	150 g/10 min	ASTM D1238
Vinyl Acetate Content	28.0 wt%	28.0 wt%	Internal Method
Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Modulus	2180 psi	15.0 MPa	ASTM D638
Tensile Elongation (Break)	> 100 %	> 100 %	ASTM D638
Hardness	Nominal Value (English)	Nominal Value (SI)	Test Method
Durometer Hardness (Shore A)	72	72	ASTM D2240
Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Continuous Use Temperature	< 392 °F	< 200 °C	
Peak Melting Temperature	151 °F	66.0 °C	ASTM D3418

Technical Data Sheet



Icorene N1016

Ethylene Vinyl Acetate Copolymer
LyondellBasell Industries
Custom Powders



Injection	Nominal Value (English)	Nominal Value (SI)
Processing (Melt) Temp	< 392 °F	< 200 °C

Notes

These are typical property values not to be construed as specification limits.

Processing Techniques

Specific recommendations for resin type and processing conditions can only be made when the end use, required properties and fabrication equipment are known.

Product Storage and Handling

- Product should be stored in dry conditions at temperatures below 50°C and protected from UV-light
- Improper storage may bring damage to the packaging and can negatively affects on the quality of this product
- Keep material completely dry for good processing

Company Information

For further information regarding the LyondellBasell company, please visit <http://www.lyb.com/>.

© LyondellBasell Industries Holdings, B.V. 2024

Disclaimer

Information in this document is accurate to the best of our knowledge at the date of publication. The document is designed to provide users general information for safe handling, use, processing, storage, transportation, disposal and release and does not constitute any warranty or quality specification, either express or implied, including any warranty of merchantability or fitness for any particular purpose. Users shall determine whether the product is suitable for their use and can be used safely and legally.

In addition to any prohibitions of use specifically noted in this document, LyondellBasell may further prohibit or restrict the sale of its products into certain applications. For further information, please contact a LyondellBasell representative.

Trademarks

The Trademark referenced within the product name is owned or used by the LyondellBasell family of companies.