

Technical Data Sheet

**Icorene N6603**

Acrylonitrile Butadiene Styrene
LyondellBasell Industries
Custom Powders

Product Description

ICORENE® N6603 is premium quality high flow ABS grade suitable for general purpose use.

This grade is suitable for masterbatch applications.

General

Material Status	• Commercial: Active
Availability	• Europe
Features	• High Flow • High Impact Resistance
Uses	• Compounding • Masterbatch
Forms	• Powder

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density	1.04 g/cm ³	1.04 g/cm ³	ISO 1183
Melt Volume-Flow Rate (MVR) (220°C/10.0 kg)	34 cm ³ /10min	34 cm ³ /10min	ISO 1133
Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Stress (Break)	4790 psi	33.0 MPa	ISO 527-2/50
Flexural Stress ¹	9430 psi	65.0 MPa	ISO 178
Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Vicat Softening Temperature ²	203 °F	95.0 °C	ISO 306/B50

Notes

¹ 0.079 in/min (2.0 mm/min)

² Oil

Notes

These are typical property values not to be construed as specification limits.

Processing Techniques

Specific recommendations for resin type and processing conditions can only be made when the end use, required properties and fabrication equipment are known.

Product Storage and Handling

- Product should be stored in dry conditions at temperatures below 50°C and protected from UV-light
- Improper storage may bring damage to the packaging and can negatively affects on the quality of this product
- Keep material completely dry for good processing

Company Information

For further information regarding the LyondellBasell company, please visit <http://www.lyb.com/>.

© LyondellBasell Industries Holdings, B.V. 2024

Disclaimer

Information in this document is accurate to the best of our knowledge at the date of publication. The document is designed to provide users general information for safe handling, use, processing, storage, transportation, disposal and release and does not constitute any warranty or quality specification, either express or implied, including any warranty of merchantability or fitness for any particular purpose. Users shall determine whether the product is suitable for their use and can be used safely and legally.

In addition to any prohibitions of use specifically noted in this document, LyondellBasell may further prohibit or restrict the sale of its products into certain applications. For further information, please contact a LyondellBasell representative.

Trademarks

The Trademark referenced within the product name is owned or used by the LyondellBasell family of companies.