

Technical Data Sheet



Icorene N7510

Polyolefin
LyondellBasell Industries
Custom Powders

Product Description

ICORENE® N7510 is an adhesive polyolefin based coating powder that has been designed for encapsulating wire goods.

This grade will provide superior adhesion to the metal without any need of primer.

ICORENE® N7510 is used for fluidized bed coating applications.

General

Material Status	• Commercial: Active		
Availability	• Europe		
Features	• Abrasion Resistant • Good Adhesion	• Good Flow • Good Processing Stability	
Uses	• Automotive Applications • Coating Applications	• Decorative Railing • Industrial Applications	• Piping • Wire & Cable Applications
Forms	• Powder		

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density	0.920 to 0.940 g/cm ³	0.920 to 0.940 g/cm ³	ASTM D1505
Apparent (Bulk) Density	0.30 to 0.35 g/cm ³	0.30 to 0.35 g/cm ³	ASTM D1895A
Appearance	smooth/glossy	smooth/glossy	Visual
Particle Size	< 11.8 mil	< 300 µm	Internal Method
Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Elongation (Break)	> 100 %	> 100 %	ASTM D638
Abrasion - (Tabor)	tba mg	tba mg	ASTM D4060
Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Gardner Impact 73°F (23°C), 0.118 in (3.00 mm)	> 88.5 in-lb	> 10.0 J	ISO 6272
Hardness	Nominal Value (English)	Nominal Value (SI)	Test Method
Durometer Hardness (Shore D)	52	52	ASTM D2240
Aging	Nominal Value (English)	Nominal Value (SI)	Test Method
Continuous Upper Temperature Resistance	140 °F	60 °C	Internal Method
Optical	Nominal Value (English)	Nominal Value (SI)	Test Method
Gloss (11.8 mil (300 µm))	60 to 90	60 to 90	ISO 2813
Cured Properties	Nominal Value (English)	Nominal Value (SI)	
Coverage - at 300µm thickness	2360 in ² /lb	3.35 m ² /kg	
Additional Information	Nominal Value (English)	Nominal Value (SI)	Test Method
Adhesion ¹	290 to 580 psi	2.00 to 4.00 MPa	
Salt Spray - resistance unscratched ²	1000 hours	1000 hours	
UV Resistance - (no significant loss of colour or gloss)	2000 hours	2000 hours	ISO 4892-2

Technical Data Sheet**Icorene N7510**

Polyolefin
LyondellBasell Industries
Custom Powders

COATING METHOD RECOMMENDATIONS**Pretreatment:**

For excellent quality finish it is essential to properly prepare your parts before coating. Metal can be either gritblasted or chemically pretreated, using suitable process in line with expected coating performance. Required information can be found on our process guideline document or through your local sales and technical contact.

Dip coating:

Preheat the metal to 250-350°C. Dip for 3-5 seconds then depending on the metal thickness a post dip heat treatment may be needed.

Automatic coating machine:

Preheat in oven at 280-350°C for 2-4 minutes. Dip for 3-5 seconds then finish in the post heat oven at 150-200°C for 2-4 minutes before final cooling in air or water.

Caution regarding heat and plastic exposure:

We recommend minimum heat history possible to achieve the desired coating finish. Excessive heat will shorten the coating lifetime and could cause discoloration. Over-thick coatings or metal parts with uneven metal thicknesses may affect the final coating properties.

CHEMICAL RESISTANCE:

- dilute acids 50°C - Fair
- dilute alkali 50°C - Fair
- salt (except peroxides) 50°C - Fair
- solvent at 23°C - Avoid contact

Notes

¹ ASTM D4541

² ISO 9227

Notes

These are typical property values not to be construed as specification limits.

Processing Techniques

Specific recommendations for resin type and processing conditions can only be made when the end use, required properties and fabrication equipment are known.

Product Storage and Handling

- Product should be stored in dry conditions at temperatures below 50°C and protected from UV-light
- Improper storage may bring damage to the packaging and can negatively affects on the quality of this product
- Keep material completely dry for good processing

Company Information

For further information regarding the LyondellBasell company, please visit <http://www.lyb.com/>.

© LyondellBasell Industries Holdings, B.V. 2024

Disclaimer

Information in this document is accurate to the best of our knowledge at the date of publication. The document is designed to provide users general information for safe handling, use, processing, storage, transportation, disposal and release and does not constitute any warranty or quality specification, either express or implied, including any warranty of merchantability or fitness for any particular purpose. Users shall determine whether the product is suitable for their use and can be used safely and legally.

In addition to any prohibitions of use specifically noted in this document, LyondellBasell may further prohibit or restrict the sale of its products into certain applications. For further information, please contact a LyondellBasell representative.

Trademarks

The Trademark referenced within the product name is owned or used by the LyondellBasell family of companies.