

Technical Data Sheet

Lupolen 5261Z Q456 B POWDER

High Density Polyethylene



Product Description

Lupolen 5261Z Q 456 B POWDER is a high density polyethylene (HDPE) with very high melt viscosity for ram extrusion of peroxide cross-linked pipes (PEX-a). The product is supplied as a nominal 25 mesh (730 µm) powder.

Regulatory Status

For regulatory compliance information, see *Lupolen 5261Z Q456 B POWDER* [Product Stewardship Bulletin \(PSB\)](#) and [Safety Data Sheet \(SDS\)](#).

Status	Commercial: Active
Availability	North America
Application	Drinking Water Pipe; Plumbing, Heating & Cooling; Underfloor Heating
Market	Industrial, Building & Construction; Pipe
Processing Method	Pipe
Attribute	High Density

Typical Properties	Nominal Value	English Units	Nominal Value	SI Units	Test Method
Physical					
Melt Flow Rate					
(190 °C/5.0 kg)	0.16	g/10 min	0.16	g/10 min	ASTM D1238
(190 °C/21.6 kg)	3	g/10 min	3	g/10 min	ASTM D1238
Density, (23 °C)	0.955	g/cm ³	0.955	g/cm ³	ASTM D1505
Mechanical					
Flexural Modulus, (2% Secant)	177000	psi	1220	MPa	ASTM D790
Tensile Modulus, (1% Secant)	191000	psi	1317	MPa	ASTM D638
Tensile Stress at Break, (23 °C)	5900	psi	40.7	MPa	ASTM D638
Tensile Stress at Yield, (23 °C)	4120	psi	28.4	MPa	ASTM D638
Tensile Elongation at Break, (23 °C)	1160	%	1160	%	ASTM D638
Tensile Elongation at Yield, (23 °C)	8	%	8	%	ASTM D638
Hardness					
Shore Hardness					
(Shore D, max)	71		71		ASTM D2240
(Shore D, 15 sec)	64		64		ASTM D2240
Thermal					
Vicat Softening Temperature					
(A1)	266	°F	130	°C	ASTM D1525
(B1)	268	°F	131	°C	ASTM D1525

Notes

LyondellBasell
Technical Data Sheet
Date: 7/25/2017

Lupolen 5261Z Q456 B POWDER
Recipient Tracking #:
Request #: 909195

All properties are on powder as-supplied and without any induced cross-linking.

These are typical property values not to be construed as specification limits.

Processing Techniques

Specific recommendations for resin type and processing conditions can only be made when the end use, required properties and fabrication equipment are known.

Company Information

For further information regarding the LyondellBasell company, please visit <http://www.lyb.com/>.

© LyondellBasell Industries Holdings, B.V. 2017

Disclaimer

Before using a product sold by a company of the LyondellBasell family of companies, users should make their own independent determination that the product is suitable for the intended use and can be used safely and legally.

SELLER MAKES NO WARRANTY; EXPRESS OR IMPLIED (INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE OR ANY WARRANTY) OTHER THAN AS SEPARATELY AGREED TO BY THE PARTIES IN A CONTRACT.

Users should review the applicable Safety Data Sheet before handling the product.

This product(s) may not be used in the manufacture of any of the following, without prior written approval by Seller for each specific product and application:

- (i) U.S. FDA Class I or II Medical Devices; Health Canada Class I, II or III Medical Devices; European Union Class I or II Medical Devices;
- (ii) film, overwrap and/or product packaging that is considered a part or component of one of the aforementioned medical devices;
- (iii) packaging in direct contact with a pharmaceutical active ingredient and/or dosage form that is intended for inhalation, injection, intravenous, nasal, ophthalmic (eye), digestive, or topical (skin) administration;
- (iv) tobacco related products and applications, electronic cigarettes and similar devices.
- (v) safety components in automotive applications, for example: air bags, air bag unit housings and covers, seat belt mechanisms, brake systems, pedals and pedal supports, steering systems.

The product(s) may not be used in:

- (i) U.S. FDA Class III Medical Devices; Health Canada Class IV Medical Devices; European Class III Medical Devices;
- (ii) applications involving permanent implantation into the body;
- (iii) life-sustaining medical applications.

All references to U.S. FDA, Health Canada, and European Union regulations include another country's equivalent regulatory classification.

In addition to the above, LyondellBasell may further prohibit or restrict the use of its products in certain applications. For further information, please contact a LyondellBasell representative.

Trademarks

Adflex, Adstif, Adsyl, Akoafloor, Akoalit, Alastian, Alathon, Alkylate, Amazing Chemistry, Aquamarine, Aquathene, Avant, Catalloy, Clyrell, CRP, Crystex, Dexflex, Duopac, Duoprime, Explore & Experiment, Filmex, Flexathene, Fueling the power to win, Glacido, Hifax, Hiflex, Histif, Hostacom, Hostalen, Hyperzone, Ideal, Indure, Integrate, Koattro, LIPP, Lucalen, Luflexen, Lupolen, Luposim, Lupostress, Lupotech, Metocene, Microthene, Moplen, MPDIOL, Nerolex, Nexprene, Petrothene, Plexar, Polymeg, Pristene, Prodflex, Pro-fax, Punctilious, Purell, Refax, SAA100, SAA101, Sequel, Softell, Spherilene, Spheripol, Spherizone, Starflex, Stretchene, Superflex, TBAC, Tebol, T-Hydro, Toppyl, Trans4m, Tufflo, Ultrathene, Vacido and Valtec are trademarks owned and/or used by the LyondellBasell family of companies.

Adsyl, Akoafloor, Akoalit, Alastian, Alathon, Aquamarine, Avant, CRP, Crystex, Dexflex, Duopac, Duoprime, Explore & Experiment, Filmex, Flexathene, Hifax, Hostacom, Hostalen, Ideal, Integrate, Koattro, Lucalen, Lupolen, Metocene, Microthene, Moplen, MPDIOL, Nexprene, Petrothene, Plexar, Polymeg, Pristene, Pro-fax, Punctilious, Purell, Sequel, Softell, Spheripol, Spherizone, Starflex, Tebol, T-Hydro, Toppyl, Tufflo and Ultrathene are registered in the U.S. Patent and Trademark Office.