

Technical Data Sheet

**Matrixx 12N6002NO**

Polypropylene Copolymer
LyondellBasell Industries
Engineering Plastics

General			
Material Status	• Commercial: Active		
Availability	• North America		
Additive	• Flame Retardant		
Features	• Flame Retardant		
UL File Number	• E51193		
Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density / Specific Gravity	0.940	0.938 g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	18 g/10 min	18 g/10 min	ASTM D1238
Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Strength			ASTM D638
Yield, 73°F (23°C), 0.125 in (3.18 mm)	3300 psi	22.8 MPa	
Tensile Elongation			ASTM D638
Yield, 73°F (23°C), 0.125 in (3.18 mm)	13 %	13 %	
Flexural Modulus - Tangent			ASTM D790
73°F (23°C), 0.125 in (3.18 mm)	170000 psi	1170 MPa	
Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Notched Izod Impact			ASTM D256
73°F (23°C), 0.125 in (3.18 mm)	2.5 ft·lb/in	130 J/m	
Gardner Impact			ASTM D5420
73°F (23°C), 0.125 in (3.18 mm)	170 in·lb	19.2 J	
Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
RTI Elec (0.06 in (1.5 mm))	239 °F	115 °C	UL 746B
RTI Imp (0.06 in (1.5 mm))	239 °F	115 °C	UL 746B
RTI Str (0.06 in (1.5 mm))	239 °F	115 °C	UL 746B
Flammability	Nominal Value (English)	Nominal Value (SI)	Test Method
Flame Rating			UL 94
0.04 in (1.0 mm)	V-2	V-2	
0.06 in (1.5 mm)	V-2	V-2	
0.12 in (3.0 mm)	V-2	V-2	

Technical Data Sheet



Matrixx 12N6002NO

Polypropylene Copolymer
LyondellBasell Industries
Engineering Plastics



Injection	Nominal Value (English)	Nominal Value (SI)
Drying Temperature	180 °F	82 °C
Drying Time	2.0 to 4.0 hr	2.0 to 4.0 hr
Processing (Melt) Temp	360 to 440 °F	182 to 227 °C
Mold Temperature	90 to 150 °F	32 to 66 °C
Injection Rate	Slow-Moderate	Slow-Moderate
Back Pressure	< 100 psi	< 0.689 MPa
Screw Speed	20 to 60 rpm	20 to 60 rpm

Notes

These are typical property values not to be construed as specification limits.

Processing Techniques

Specific recommendations for resin type and processing conditions can only be made when the end use, required properties and fabrication equipment are known.

Product Storage and Handling

- Product should be stored in dry conditions at temperatures below 50°C and protected from UV-light
- Improper storage may bring damage to the packaging and can negatively affects on the quality of this product
- Keep material completely dry for good processing

Company Information

For further information regarding the LyondellBasell company, please visit <http://www.lyb.com/>.

© LyondellBasell Industries Holdings, B.V. 2024

Disclaimer

Information in this document is accurate to the best of our knowledge at the date of publication. The document is designed to provide users general information for safe handling, use, processing, storage, transportation, disposal and release and does not constitute any warranty or quality specification, either express or implied, including any warranty of merchantability or fitness for any particular purpose. Users shall determine whether the product is suitable for their use and can be used safely and legally.

In addition to any prohibitions of use specifically noted in this document, LyondellBasell may further prohibit or restrict the sale of its products into certain applications. For further information, please contact a LyondellBasell representative.

Trademarks

The Trademark referenced within the product name is owned or used by the LyondellBasell family of companies.