

Technical Data Sheet

**Matrixx 54S7102**

Polycarbonate
LyondellBasell Industries
Engineering Plastics

General			
Material Status	• Commercial: Active		
Availability	• North America		
Filler / Reinforcement	• Glass Fiber, 10% Filler by Weight		
Additive	• Flame Retardant		
Features	• Flame Retardant		
Forms	• Pellets		
Processing Method	• Injection Molding		
Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density / Specific Gravity	1.26	1.26 g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (300°C/1.2 kg)	12 g/10 min	12 g/10 min	ASTM D1238
Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Strength (Yield)	9000 psi	62.1 MPa	ASTM D638
Flexural Modulus	480000 psi	3310 MPa	ASTM D790
Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Notched Izod Impact	2.0 ft·lb/in	110 J/m	ASTM D256
Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Deflection Temperature Under Load			ASTM D648
66 psi (0.45 MPa), Unannealed	290 °F	143 °C	
264 psi (1.8 MPa), Unannealed	285 °F	141 °C	
RTI Str	200 °F	93.3 °C	UL 746B
Flammability	Nominal Value (English)	Nominal Value (SI)	Test Method
Flame Rating (0.06 in (1.5 mm))	V-0	V-0	UL 94

Technical Data Sheet



Matrixx 54S7102

Polycarbonate
LyondellBasell Industries
Engineering Plastics



Injection	Nominal Value (English)	Nominal Value (SI)
Drying Temperature	250 °F	121 °C
Drying Time	4.0 to 6.0 hr	4.0 to 6.0 hr
Rear Temperature	540 to 590 °F	282 to 310 °C
Middle Temperature	540 to 590 °F	282 to 310 °C
Front Temperature	540 to 590 °F	282 to 310 °C
Processing (Melt) Temp	560 to 610 °F	293 to 321 °C
Mold Temperature	160 to 220 °F	71 to 104 °C
Injection Rate	Slow-Moderate	Slow-Moderate
Back Pressure	50.0 to 100 psi	0.345 to 0.689 MPa
Screw Speed	40 to 75 rpm	40 to 75 rpm
Cushion	0.250 to 0.500 in	6.35 to 12.7 mm

Injection Notes

-20°F Dewpoint

Notes

These are typical property values not to be construed as specification limits.

Processing Techniques

Specific recommendations for resin type and processing conditions can only be made when the end use, required properties and fabrication equipment are known.

Product Storage and Handling

- Product should be stored in dry conditions at temperatures below 50°C and protected from UV-light
- Improper storage may bring damage to the packaging and can negatively affects on the quality of this product
- Keep material completely dry for good processing

Company Information

For further information regarding the LyondellBasell company, please visit <http://www.lyb.com/>.

© LyondellBasell Industries Holdings, B.V. 2024

Disclaimer

Information in this document is accurate to the best of our knowledge at the date of publication. The document is designed to provide users general information for safe handling, use, processing, storage, transportation, disposal and release and does not constitute any warranty or quality specification, either express or implied, including any warranty of merchantability or fitness for any particular purpose. Users shall determine whether the product is suitable for their use and can be used safely and legally.

In addition to any prohibitions of use specifically noted in this document, LyondellBasell may further prohibit or restrict the sale of its products into certain applications. For further information, please contact a LyondellBasell representative.

Trademarks

The Trademark referenced within the product name is owned or used by the LyondellBasell family of companies.

Page: 2 of 2
LyondellBasell

www.lyondellbasell.com
Publish Date: 2024-03-14