

Technical Data Sheet

**Matrixx 662E0**

Polyamide 66
LyondellBasell Industries
Engineering Plastics

General			
Material Status	• Commercial: Active		
Availability	• North America		
Forms	• Pellets		
Processing Method	• Injection Molding		
Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density / Specific Gravity	1.14	1.14 g/cm ³	ASTM D792
Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Strength (Yield)	11500 psi	79.3 MPa	ASTM D638
Flexural Modulus - Tangent	425000 psi	2930 MPa	ASTM D790
Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Notched Izod Impact	1.1 ft-lb/in	59 J/m	ASTM D256
Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Deflection Temperature Under Load			ASTM D648
66 psi (0.45 MPa), Unannealed	385 °F	196 °C	
264 psi (1.8 MPa), Unannealed	158 °F	70.0 °C	

Technical Data Sheet



Matrixx 662E0

Polyamide 66
LyondellBasell Industries
Engineering Plastics



Injection	Nominal Value (English)	Nominal Value (SI)
Drying Temperature	160 to 180 °F	71 to 82 °C
Drying Time	4.0 hr	4.0 hr
Rear Temperature	480 to 560 °F	249 to 293 °C
Middle Temperature	480 to 560 °F	249 to 293 °C
Front Temperature	480 to 560 °F	249 to 293 °C
Processing (Melt) Temp	520 to 560 °F	271 to 293 °C
Mold Temperature	125 to 180 °F	52 to 82 °C
Injection Rate	Moderate-Fast	Moderate-Fast
Back Pressure	< 100 psi	< 0.689 MPa
Cushion	0.125 to 0.250 in	3.18 to 6.35 mm

Injection Notes

- 20°C Dewpoint
- Screw Speed: Medium

Notes

These are typical property values not to be construed as specification limits.

Processing Techniques

Specific recommendations for resin type and processing conditions can only be made when the end use, required properties and fabrication equipment are known.

Product Storage and Handling

- Product should be stored in dry conditions at temperatures below 50°C and protected from UV-light
- Improper storage may bring damage to the packaging and can negatively affects on the quality of this product
- Keep material completely dry for good processing

Company Information

For further information regarding the LyondellBasell company, please visit <http://www.lyb.com/>.

© LyondellBasell Industries Holdings, B.V. 2024

Disclaimer

Information in this document is accurate to the best of our knowledge at the date of publication. The document is designed to provide users general information for safe handling, use, processing, storage, transportation, disposal and release and does not constitute any warranty or quality specification, either express or implied, including any warranty of merchantability or fitness for any particular purpose. Users shall determine whether the product is suitable for their use and can be used safely and legally.

In addition to any prohibitions of use specifically noted in this document, LyondellBasell may further prohibit or restrict the sale of its products into certain applications. For further information, please contact a LyondellBasell representative.

Trademarks

The Trademark referenced within the product name is owned or used by the LyondellBasell family of companies.

Page: 2 of 2
LyondellBasell

www.lyondellbasell.com
Publish Date: 2024-03-14