

Technical Data Sheet

**Microthene MP625962**

Linear Low Density Polyethylene
LyondellBasell Industries
Engineering Plastics

Product Description

Microthene MP625962 is a hexene LLDPE rotational molding powder with excellent flow properties selected by customers to produce a variety of objects such as toys, playground equipment, drums and agricultural and chemical storage containers. MP625962 exhibits high ESCR, low temperature impact strength and warp resistance. MP625962 is a UV-stabilized, 35-mesh powder and is also available in pellet form as Petrothene GA625962.

General

Material Status	• Commercial: Active		
Availability	• North America		
Additive	• UV Stabilizer		
Features	• Good Flow • Hexene Comonomer	• High ESCR (Stress Crack Resist.) • Low Temperature Impact Resistance	• Warp Resistant
Uses	• Agricultural Applications • Containers	• Industrial Containers • Toys	
Forms	• Powder		

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density	0.935 g/cm ³	0.935 g/cm ³	ASTM D1505
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	5.0 g/10 min	5.0 g/10 min	ASTM D1238
Environmental Stress-Cracking Resistance (ESCR) 100% Igepal CO-630, F50	> 1000 hr	> 1000 hr	ASTM D1693A
Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Strength ¹ (Yield)	2700 psi	18.6 MPa	ASTM D638
Flexural Modulus			ASTM D790
1% Secant	105000 psi	724 MPa	
2% Secant	91000 psi	627 MPa	
Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Impact Strength			ARM
-40°F (-40°C), 0.125 in (3.18 mm)	40 ft-lb	54 J	
-40°F (-40°C), 0.250 in (6.35 mm)	155 ft-lb	210 J	
Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Deflection Temperature Under Load			ASTM D648
66 psi (0.45 MPa), Unannealed	131 °F	55.0 °C	
264 psi (1.8 MPa), Unannealed	102 °F	39.0 °C	

Notes

¹ 2.0 in/min (51 mm/min)

Notes

These are typical property values not to be construed as specification limits.

Processing Techniques

Specific recommendations for resin type and processing conditions can only be made when the end use, required properties and fabrication equipment are known.

Product Storage and Handling

- Product should be stored in dry conditions at temperatures below 50°C and protected from UV-light
- Improper storage may bring damage to the packaging and can negatively affects on the quality of this product
- Keep material completely dry for good processing

Company Information

For further information regarding the LyondellBasell company, please visit <http://www.lyb.com/>.

© LyondellBasell Industries Holdings, B.V. 2024

Page: 1 of 2
LyondellBasell

www.lyondellbasell.com
Publish Date: 2024-03-14

Technical Data Sheet

**Microthene MP625962**

Linear Low Density Polyethylene
LyondellBasell Industries
Engineering Plastics

Disclaimer

Information in this document is accurate to the best of our knowledge at the date of publication. The document is designed to provide users general information for safe handling, use, processing, storage, transportation, disposal and release and does not constitute any warranty or quality specification, either express or implied, including any warranty of merchantability or fitness for any particular purpose. Users shall determine whether the product is suitable for their use and can be used safely and legally.

In addition to any prohibitions of use specifically noted in this document, LyondellBasell may further prohibit or restrict the sale of its products into certain applications. For further information, please contact a LyondellBasell representative.

Trademarks

The Trademark referenced within the product name is owned or used by the LyondellBasell family of companies.