

## Technical Data Sheet

### *Moplen* HP740T

Polypropylene, Homopolymer



#### Product Description

*Moplen* HP740T is a polypropylene homopolymer with outstanding flowability, excellent transparency, high gloss, and high stiffness. Typical customer applications are rigid packaging, thin wall injection molding (TWIM) of food trays, drinking cups, plastic files, DVD casing.

#### Regulatory Status

For regulatory compliance information, see *Moplen* HP740T [Product Stewardship Bulletin \(PSB\) and Safety Data Sheet \(SDS\)](#).

|                          |                                                                                           |
|--------------------------|-------------------------------------------------------------------------------------------|
| <b>Status</b>            | Commercial: Active                                                                        |
| <b>Availability</b>      | Africa-Middle East; Asia-Pacific; Australia and New Zealand                               |
| <b>Application</b>       | Clear Containers; Housewares; Opaque Containers                                           |
| <b>Market</b>            | Consumer Products; Rigid Packaging                                                        |
| <b>Processing Method</b> | Injection Molding                                                                         |
| <b>Attribute</b>         | Fast Cycle (Production); High Clarity; High Flow; High Gloss; High Stiffness; Homopolymer |

| Typical Properties                                           | Nominal Value | Units             | Test Method |
|--------------------------------------------------------------|---------------|-------------------|-------------|
| <b>Physical</b>                                              |               |                   |             |
| Melt Flow Rate, (230 °C/2.16 kg)                             | 60            | g/10 min          | ASTM D1238  |
| Density                                                      | 0.90          | g/cm <sup>3</sup> | ASTM D792   |
| <b>Mechanical</b>                                            |               |                   |             |
| Flexural Modulus                                             | 1800          | MPa               | ASTM D790   |
| Tensile Strength at Yield                                    | 37            | MPa               | ASTM D638   |
| Tensile Elongation at Yield                                  | 10            | %                 | ASTM D638   |
| <b>Impact</b>                                                |               |                   |             |
| Notched Izod Impact Strength, (23 °C)                        | 20            | J/m               | ASTM D256   |
| <b>Hardness</b>                                              |               |                   |             |
| Rockwell Hardness, (R-Scale)                                 | 105           |                   | ASTM D785   |
| <b>Thermal</b>                                               |               |                   |             |
| Deflection Temperature Under Load, (0.46 N/mm <sup>2</sup> ) | 125           | °C                | ASTM D648   |

#### Notes

These are typical property values not to be construed as specification limits.

## Company Information

For further information regarding the LyondellBasell company, please visit <http://www.lyb.com/>.

© LyondellBasell Industries Holdings, B.V. 2017

## Disclaimer

Before using a product sold by a company of the LyondellBasell family of companies, users should make their own independent determination that the product is suitable for the intended use and can be used safely and legally.

SELLER MAKES NO WARRANTY; EXPRESS OR IMPLIED (INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE OR ANY WARRANTY) OTHER THAN AS SEPARATELY AGREED TO BY THE PARTIES IN A CONTRACT.

Users should review the applicable Safety Data Sheet before handling the product.

This product(s) may not be used in the manufacture of any of the following, without prior written approval by Seller for each specific product and application:

- (i) U.S. FDA Class I or II Medical Devices; Health Canada Class I, II or III Medical Devices; European Union Class I or II Medical Devices;
- (ii) film, overwrap and/or product packaging that is considered a part or component of one of the aforementioned medical devices;
- (iii) packaging in direct contact with a pharmaceutical active ingredient and/or dosage form that is intended for inhalation, injection, intravenous, nasal, ophthalmic (eye), digestive, or topical (skin) administration;
- (iv) tobacco related products and applications, electronic cigarettes and similar devices.
- (v) safety components in automotive applications, for example: air bags, air bag unit housings and covers, seat belt mechanisms, brake systems, pedals and pedal supports, steering systems.

The product(s) may not be used in:

- (i) U.S. FDA Class III Medical Devices; Health Canada Class IV Medical Devices; European Class III Medical Devices;
- (ii) applications involving permanent implantation into the body;
- (iii) life-sustaining medical applications.

All references to U.S. FDA, Health Canada, and European Union regulations include another country's equivalent regulatory classification.

In addition to the above, LyondellBasell may further prohibit or restrict the use of its products in certain applications. For further information, please contact a LyondellBasell representative.

## Trademarks

*Adflex, Adstif, Adsyl, Akoafloor, Akoalit, Alastian, Alathon, Alkylate, Amazing Chemistry, Aquamarine, Aquathene, Avant, Catalloy, Clyrell, CRP, Crystex, Dexflex, Duopac, Duoprime, Explore & Experiment, Filmex, Flexathene, Fueling the power to win, Glacido, Hifax, Hiflex, Histif, Hostacom, Hostalen, Hyperzone, Ideal, Indure, Integrate, Koattro, LIPP, Lucalen, Luflexen, Lupolen, Luposim, Lupostress, Lupotech, Metocene, Microthene, Moplen, MPDIOL, Nerolex, Nexprene, Petrothene, Plexar, Polymeg, Pristene, Prodflex, Pro-fax, Punctilious, Purell, Refax, SAA100, SAA101, Sequel, Softell, Spherilene, Spheripol, Spherizone, Starflex, Stretchene, Superflex, TBAC, Tebol, T-Hydro, Toppyl, Trans4m, Tufflo, Ultrathene, Vacido and Valtec* are trademarks owned and/or used by the LyondellBasell family of companies.

*Adsyl, Akoafloor, Akoalit, Alastian, Alathon, Aquamarine, Avant, CRP, Crystex, Dexflex, Duopac, Duoprime, Explore & Experiment, Filmex, Flexathene, Hifax, Hostacom, Hostalen, Ideal, Integrate, Koattro, Lucalen, Lupolen, Metocene, Microthene, Moplen, MPDIOL, Nexprene, Petrothene, Plexar, Polymeg, Pristene, Pro-fax, Punctilious, Purell, Sequel, Softell, Spheripol, Spherizone, Starflex, Tebol, T-Hydro, Toppyl, Tufflo and Ultrathene* are registered in the U.S. Patent and Trademark Office.