



Moplen RP225M

Polypropylene, Random Copolymer

Product Description

"Moplen" RP225M is a controlled rheology medium modified propylene random copolymer for manufacturing high transparent cast films. The product contains slip and anti-block agents. It offers good processability, excellent clarity and gloss and exhibits very good heat weldability. Main applications are packaging of foodstuffs, packaging of stationary, shirts and hosiery. It is also suitable for production of stationary folders.
"Moplen" RP225M is suitable for food contact.
For regulatory information please refer to "Moplen" RP225M Product Stewardship Bulletin (PSB).

Product Characteristics

Status	Commercial: Active
Test Method used	ISO ASTM
Availability	Europe, Africa-Middle East
Processing Methods	Cast Film
Features	Unspecified Antiblocking , High Clarity, Controlled Rheology, Random Copolymer, High Gloss , Good Processability, Unspecified Slip, Weldable
Typical Customer Applications	Cast Film, Food Packaging Film, Stationery Film, Textile Packaging Film

Typical Properties	Method	Value	Unit
Mechanical			
Tensile Strength @ Brk MD	ASTM D 882	38.0	MPa
Tensile Strength @ Yld MD	ASTM D 882	19.4	MPa
Elongation at break MD	ASTM D 882	740	%
Optical			
Haze (50 µ)	ASTM D 1003	<1.5	%
Gloss (45°, 50 µ)	ASTM D 2457	89	
Film			
Coefficient of Friction	ASTM D 1894	0.20 0.20	
Secant modulus MD (30 mm/min, 50 µ)	ASTM D 882	560	MPa

Additional Properties

Typical film properties of laboratory casting line:
Gloss 45°, ASTM D 2457, 50 µm: 89
Haze, ASTM D 1003, 50 µm: <1.5%
Tensile Young modulus, ASTM D 882, 25 mm/min, 50 µm: 560 MPa
Stress at Yield, ASTM D 882, 500 mm/min, 50 µm, 19.4 MPa
Elongation at Yield, ASTM D 882, 500 mm/min, 50 µm: 7.6%
Stress at break, ASTM D 882, 500 mm/min, 50 µm, 38 MPa
Elongation at break, ASTM D 882, 500 mm/min, 50 µm: 740%
Coefficient of friction, ASTM D 1894, Static: 0.2
Coefficient of friction, ASTM D 1894, Dynamic: 0.2

Notes

Typical properties; not to be construed as specifications.

© LyondellBasell Industries Holdings, B.V. 2014

LyondellBasell markets this product through the following entities:

- Equistar Chemicals, LP
- Basell Sales & Marketing Company B.V.
- Basell Asia Pacific Limited
- Basell International Trading FZE
- LyondellBasell Australia Pty Ltd

For the contact details of the LyondellBasell company selling this product in your country, please visit <http://www.lyb.com/>.

Before using a product sold by a company of the LyondellBasell family of companies, users should make their own independent determination that the product is suitable for the intended use and can be used safely and legally.

SELLER MAKES NO WARRANTY; EXPRESS OR IMPLIED (INCLUDING ANY WARRANTY OF

MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE OR ANY WARRANTY) OTHER THAN AS SEPARATELY AGREED TO BY THE PARTIES IN A CONTRACT.

This product(s) may not be used in:

(i) any U.S. FDA Class I, Health Canada Class I, and/or European Union Class I Medical Devices, without prior notification to Seller for each specific product and application; or

(ii) the manufacture of any of the following, without prior written approval by Seller for each specific product and application: (1) U.S. FDA Class II, Health Canada Class II or Class III, and/or European Union Class II Medical Devices; (2) film, overwrap and/or product packaging that is considered a part or component of one of the aforementioned Medical Devices; (3) packaging in direct contact with a pharmaceutical active ingredient and/or dosage form that is intended for inhalation, injection, intravenous, nasal, ophthalmic (eye), digestive, or topical (skin) administration; (4) tobacco related products and applications; (5) electronic cigarettes and similar devices; and (6) pressure pipe or fittings that are considered a part or component of a nuclear reactor.

(iii) Additionally, the product(s) may not be used in: (1) U.S. FDA Class III, Health Canada Class IV, and/or European Class III Medical Devices; (2) applications involving permanent implantation into the body; (3) life-sustaining medical applications; and (4) lead, asbestos or MTBE related applications.

All references to U.S. FDA, Health Canada, and European Union regulations include another country's equivalent regulatory classification.

Users should review the applicable Material Safety Data Sheet before handling the product.

Addhere, Adflex, Adstif, Adsyl, Akoafloor, Akoalit, Alastian, Alathon, Alkylate, Amazing Chemistry, Aquamarine, Aquathene, Arctic Plus, Arctic Shield, Avant, Catalloy, Clyrell, CRP, Crystex, Dexflex, Duopac, Duoprime, Explore & Experiment, Filmex, Flexathene, Fueling the power to win, Get in touch with, Glacido, Hifax, Histif, Hostacom, Hostalen PP, Hostalen ACP, Ideal, Indure, Integrate, Koattro, LIPP, Lucalen, Lufflexen, Lupolen, Lupolex, Luposim, Lupostress, Lupotech, Metocene, Microthene, Moplen, MPDIOL, Nerolex, Nexprene, Petrothene, Plexar, Polymeg, Pristene, Prodflex, Pro-fax, Punctilious, Purell, Refax, SAA100, SAA101, Sequel, Softell, Spherilene, Spheripol, Spherizone, Starflex, Stretchene, Superflex, TBAC, Tebol, T-Hydro, Toppyl, Trans4m, Tufflo, Ultrathene, Vacido and Valtec, are trademarks owned and/or used by the LyondellBasell family of companies.

Adsyl, Akoafloor, Akoalit, Alastian, Alathon, Aquamarine, Arctic Plus, Arctic Shield, Avant, CRP, Crystex, Dexflex, Duopac, Duoprime, Explore & Experiment, Filmex, Flexathene, Hifax, Hostacom, Hostalen, Ideal, Integrate, Koattro, Lucalen, Lupolen, Metocene, Microthene, Moplen, MPDIOL, Nexprene, Petrothene, Plexar, Polymeg, Pristene, Pro-fax, Punctilious, Purell, Sequel, Softell, Spheripol, Spherizone, Starflex, Tebol, T-Hydro, Toppyl, Tufflo, Ultrathene are registered in the U.S. Patent and Trademark Office.

Release Date: 16 May 2013