

Technical Data Sheet

**Perlex R3530**

Polycarbonate
LyondellBasell Industries
Engineering Plastics

General			
Material Status	• Commercial: Active		
Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Filler / Reinforcement	• Glass Fiber, 30% Filler by Weight		
Additive	• Flame Retardant		
Features	• Flame Retardant		
Uses	• Machine/Mechanical Parts		
Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density	1.35 g/cm ³	1.35 g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (300°C/1.2 kg)	10 g/10 min	10 g/10 min	ISO 1133
Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Modulus	1.22E+6 psi	8400 MPa	ISO 527-1
Tensile Stress (Yield)	13800 psi	95.0 MPa	ISO 527-2
Flexural Modulus	1.16E+6 psi	8000 MPa	ISO 178
Flexural Stress	25400 psi	175 MPa	ISO 178
Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Notched Izod Impact (Area) (73°F (23°C))	4.76 ft·lb/in ²	10.0 kJ/m ²	ASTM D256
Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Deflection Temperature Under Load			
66 psi (0.45 MPa), Unannealed	300 °F	149 °C	ISO 75-2/B
264 psi (1.8 MPa), Unannealed	289 °F	143 °C	ISO 75-2/A
Vicat Softening Temperature	293 °F	145 °C	ISO 306/B50
Flammability	Nominal Value (English)	Nominal Value (SI)	Test Method
Burning Rate			
0.0787 in (2.00 mm)	< 3.9 in/min	< 100 mm/min	ISO 3795
0.0787 in (2.00 mm)	< 3.9 in/min	< 100 mm/min	FMVSS 302
Flame Rating			UL 94
0.06 in (1.6 mm)	V-0	V-0	
0.13 in (3.2 mm)	V-0	V-0	
Glow Wire Ignition Temperature			IEC 60695-2-13
0.04 in (1.0 mm)	1560 °F	850 °C	
0.08 in (2.0 mm)	1560 °F	850 °C	
0.12 in (3.0 mm)	1560 °F	850 °C	

Notes

These are typical property values not to be construed as specification limits.

Processing Techniques

Specific recommendations for resin type and processing conditions can only be made when the end use, required properties and fabrication equipment are known.

Product Storage and Handling

- Product should be stored in dry conditions at temperatures below 50°C and protected from UV-light
- Improper storage may bring damage to the packaging and can negatively affects on the quality of this product
- Keep material completely dry for good processing

Company Information

For further information regarding the LyondellBasell company, please visit <http://www.lyb.com/>.

© LyondellBasell Industries Holdings, B.V. 2024

Page: 1 of 2
LyondellBasell

www.lyondellbasell.com
Publish Date: 2024-03-14

Technical Data Sheet



Perlex R3530

Polycarbonate
LyondellBasell Industries
Engineering Plastics

Disclaimer

Information in this document is accurate to the best of our knowledge at the date of publication. The document is designed to provide users general information for safe handling, use, processing, storage, transportation, disposal and release and does not constitute any warranty or quality specification, either express or implied, including any warranty of merchantability or fitness for any particular purpose. Users shall determine whether the product is suitable for their use and can be used safely and legally.

In addition to any prohibitions of use specifically noted in this document, LyondellBasell may further prohibit or restrict the sale of its products into certain applications. For further information, please contact a LyondellBasell representative.

Trademarks

The Trademark referenced within the product name is owned or used by the LyondellBasell family of companies.