

Technical Data Sheet



Polyaxis CP 812

Linear Low Density Polyethylene
LyondellBasell Industries
Rotomolding

Product Description

Polyaxis CP 812 is a general purpose linear low density polyethylene compound offering quick cycles and part to part consistency. Available as pellet or powder.

General

Material Status	• Commercial: Active
Availability	• North America
Additive	• Long Term UV-8 Stabilizer: Yes
Features	• Fast Molding Cycle
Uses	• General Purpose
UL File NumberUSA	• E 51193
Appearance	• Colors Available
Forms	• Pellets • Powder
Processing Method	• Rotational Molding

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density ¹	0.932 to 0.939 g/cm ³	0.932 to 0.939 g/cm ³	ASTM D1505
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	5.0 to 7.0 g/10 min	5.0 to 7.0 g/10 min	ASTM D1238
Environmental Stress-Cracking Resistance (ESCR)			ASTM D1693
10% Igepal, Compression Molded, F50	> 25.0 hr	> 25.0 hr	
100% Igepal, Compression Molded, F50	> 500 hr	> 500 hr	
Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Strength ² (Yield, Rotational Molded)	2250 psi	15.5 MPa	ASTM D638
Tensile Elongation ²			ASTM D638
Break, Rotational Molded	500 %	500 %	
Flexural Modulus - 1% Secant (Rotational Molded)	85000 psi	586 MPa	ASTM D790
Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Impact Strength			ARM
-40°F (-40°C), 0.125 in (3.18 mm), Rotational Molded	56 ft·lb	76 J	
-40°F (-40°C), 0.250 in (6.35 mm), Rotational Molded	145 ft·lb	197 J	
Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Deflection Temperature Under Load			ASTM D648
66 psi (0.45 MPa), Unannealed, 0.00492 in (0.125 mm), Rotational Molded	129 °F	54.0 °C	
264 psi (1.8 MPa), Unannealed, 0.00492 in (0.125 mm), Rotational Molded	96.8 °F	36.0 °C	
Flammability	Nominal Value (English)	Nominal Value (SI)	Test Method
Flame Rating (0.06 in (1.5 mm), ALL)	HB	HB	UL 94

Notes

¹ Compression Molded

² 2.0 in/min (51 mm/min)

Notes

These are typical property values not to be construed as specification limits.

Processing Techniques

Specific recommendations for resin type and processing conditions can only be made when the end use, required properties and fabrication equipment are known.

Product Storage and Handling

Technical Data Sheet



Polyaxis CP 812

Linear Low Density Polyethylene
LyondellBasell Industries
Rotomolding

- Product should be stored in dry conditions at temperatures below 50°C and protected from UV-light
- Improper storage may bring damage to the packaging and can negatively affects on the quality of this product
- Keep material completely dry for good processing

Company Information

For further information regarding the LyondellBasell company, please visit <http://www.lyb.com/>.

© LyondellBasell Industries Holdings, B.V. 2024

Disclaimer

Information in this document is accurate to the best of our knowledge at the date of publication. The document is designed to provide users general information for safe handling, use, processing, storage, transportation, disposal and release and does not constitute any warranty or quality specification, either express or implied, including any warranty of merchantability or fitness for any particular purpose. Users shall determine whether the product is suitable for their use and can be used safely and legally.

In addition to any prohibitions of use specifically noted in this document, LyondellBasell may further prohibit or restrict the sale of its products into certain applications. For further information, please contact a LyondellBasell representative.

Trademarks

The Trademark referenced within the product name is owned or used by the LyondellBasell family of companies.