

Technical Data Sheet



Polyaxis LL 3568

Linear Low Density Polyethylene
LyondellBasell Industries
Rotomolding

Product Description

PolyAxis LL 3568 is a linear low density polyethylene intended for the rotational molding industry. Offers excellent ESCR and toughness.

General

Material Status	• Commercial: Active
Availability	• North America
Features	• Good ESCR (Stress Crack Resist.) • Good Toughness • Hexene Comonomer • UV Resistant
Uses	• Displays • General Purpose • Outdoor Applications • Toys
Appearance	• Colors Available
Forms	• Powder
Processing Method	• Rotational Molding

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density / Specific Gravity	0.936	0.934 g/cm ³	ASTM D1505
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	6.8 g/10 min	6.8 g/10 min	ASTM D1238
Environmental Stress-Cracking Resistance (ESCR)			ASTM D1693
10% Igepal, Compression Molded, F50	50.0 hr	50.0 hr	
100% Igepal, Compression Molded, F50	> 1000 hr	> 1000 hr	
Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Strength ¹ (Yield, Rotational Molded)	2300 psi	15.9 MPa	ASTM D638
Tensile Elongation ² (Yield)	10 %	10 %	ASTM D638
Flexural Modulus - 1% Secant (Rotational Molded)	83000 psi	572 MPa	ASTM D790
Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Impact Strength			ARM
-40°F (-40°C), 0.125 in (3.18 mm), Rotational Molded	58 ft·lb	79 J	
-40°F (-40°C), 0.250 in (6.35 mm), Rotational Molded	> 148 ft·lb	> 200 J	
Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Deflection Temperature Under Load			ASTM D648
66 psi (0.45 MPa), Unannealed	126 °F	52.2 °C	
264 psi (1.8 MPa), Unannealed	97.0 °F	36.1 °C	
Peak Melting Temperature	259 °F	126 °C	ASTM D3418

Notes

¹ 2.0 in/min (50 mm/min)

² 2.0 in/min (51 mm/min)

Notes

These are typical property values not to be construed as specification limits.

Processing Techniques

Specific recommendations for resin type and processing conditions can only be made when the end use, required properties and fabrication equipment are known.

Product Storage and Handling

- Product should be stored in dry conditions at temperatures below 50°C and protected from UV-light
- Improper storage may bring damage to the packaging and can negatively affects on the quality of this product
- Keep material completely dry for good processing

Company Information

Page: 1 of 2
LyondellBasell

www.lyondellbasell.com
Publish Date: 2024-03-14

Technical Data Sheet

**Polyaxis LL 3568**

Linear Low Density Polyethylene
LyondellBasell Industries
Rotomolding

For further information regarding the LyondellBasell company, please visit <http://www.lyb.com/>.

© LyondellBasell Industries Holdings, B.V. 2024

Disclaimer

Information in this document is accurate to the best of our knowledge at the date of publication. The document is designed to provide users general information for safe handling, use, processing, storage, transportation, disposal and release and does not constitute any warranty or quality specification, either express or implied, including any warranty of merchantability or fitness for any particular purpose. Users shall determine whether the product is suitable for their use and can be used safely and legally.

In addition to any prohibitions of use specifically noted in this document, LyondellBasell may further prohibit or restrict the sale of its products into certain applications. For further information, please contact a LyondellBasell representative.

Trademarks

The Trademark referenced within the product name is owned or used by the LyondellBasell family of companies.