

Technical Data Sheet



Polyflam RIPP 374 ND CS1 GREY 64540 K3020

Polypropylene Copolymer
LyondellBasell Industries
Engineering Plastics

Product Description

20% talc filled flame-retardant PP-Copolymer; without PBDE

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Filler / Reinforcement	• Talc, 20% Filler by Weight		
Features	• Copolymer	• Copper Contact Stabilized	• Flame Retardant
UL File Number	• E86615		
Processing Method	• Injection Molding		
Resin ID (ISO 1043)	• PP TD20 FR(17)		

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density	1.44 g/cm ³	1.44 g/cm ³	ISO 1183/A
Melt Volume-Flow Rate (MVR) (230°C/2.16 kg)	12 cm ³ /10min	12 cm ³ /10min	ISO 1133
Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Modulus	319000 psi	2200 MPa	ISO 527-1/1A/1
Tensile Stress (Yield)	2760 psi	19.0 MPa	ISO 527-2/1A/50
Tensile Strain (Yield)	1.6 %	1.6 %	ISO 527-2/1A/50
Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Charpy Unnotched Impact Strength 73°F (23°C)	19 ft·lb/in ²	40 kJ/m ²	ISO 179/1eU
Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Vicat Softening Temperature	289 °F	143 °C	ISO 306/A50
Ball Pressure Test (212°F (100°C))	Pass	Pass	IEC 60695-10-2
RTI Elec			UL 746B
0.06 in (1.5 mm)	122 °F	50.0 °C	
0.12 in (3.0 mm)	122 °F	50.0 °C	
RTI Imp			UL 746B
0.06 in (1.5 mm)	122 °F	50.0 °C	
0.12 in (3.0 mm)	122 °F	50.0 °C	
RTI Str			UL 746B
0.06 in (1.5 mm)	122 °F	50.0 °C	
0.12 in (3.0 mm)	122 °F	50.0 °C	
Electrical	Nominal Value (English)	Nominal Value (SI)	Test Method
Comparative Tracking Index	600 V	600 V	IEC 60112
Flammability	Nominal Value (English)	Nominal Value (SI)	Test Method
Burning Rate			ISO 3795
0.0591 in (1.50 mm), Self-Extinguishing	0.0 in/min	0.0 mm/min	
0.118 in (3.00 mm), Self-Extinguishing	0.0 in/min	0.0 mm/min	
Flame Rating			
0.031 in (0.8 mm)	V-0	V-0	UL 94
0.06 in (1.5 mm)	V-0	V-0	UL 94 IEC 60695-11-10, -20
0.12 in (3.0 mm)	V-0	V-0	UL 94 IEC 60695-11-10, -20
0.03 in (0.8 mm)	V-0	V-0	IEC 60695-11-10, -20

Technical Data Sheet**Polyflam RIPP 374 ND CS1 GREY 64540 K3020**

Polypropylene Copolymer
LyondellBasell Industries
Engineering Plastics

Flammability	Nominal Value (English)	Nominal Value (SI)	Test Method
Glow Wire Flammability Index			IEC 60695-2-12
0.06 in (1.5 mm)	1760 °F	960 °C	
0.12 in (3.0 mm)	1760 °F	960 °C	
Glow Wire Ignition Temperature			IEC 60695-2-13
0.06 in (1.5 mm)	1380 °F	750 °C	
0.12 in (3.0 mm)	1380 °F	750 °C	
Oxygen Index	27 %	27 %	ISO 4589-2

Technical Data Sheet



Polyflam RIPP 374 ND CS1 GREY 64540 K3020

Polypropylene Copolymer
LyondellBasell Industries
Engineering Plastics



Injection	Nominal Value (English)	Nominal Value (SI)
Drying Temperature	158 to 176 °F	70 to 80 °C
Drying Time	2.0 to 4.0 hr	2.0 to 4.0 hr
Processing (Melt) Temp	356 to 428 °F	180 to 220 °C
Mold Temperature	104 to 176 °F	40 to 80 °C

Injection Notes

Mould surface contacting melt should be of non-corrosive steel (content of chrome > 12%)

Notes

These are typical property values not to be construed as specification limits.

Processing Techniques

Specific recommendations for resin type and processing conditions can only be made when the end use, required properties and fabrication equipment are known.

Product Storage and Handling

- Product should be stored in dry conditions at temperatures below 50°C and protected from UV-light
- Improper storage may bring damage to the packaging and can negatively affects on the quality of this product
- Keep material completely dry for good processing

Company Information

For further information regarding the LyondellBasell company, please visit <http://www.lyb.com/>.

© LyondellBasell Industries Holdings, B.V. 2024

Disclaimer

Information in this document is accurate to the best of our knowledge at the date of publication. The document is designed to provide users general information for safe handling, use, processing, storage, transportation, disposal and release and does not constitute any warranty or quality specification, either express or implied, including any warranty of merchantability or fitness for any particular purpose. Users shall determine whether the product is suitable for their use and can be used safely and legally.

In addition to any prohibitions of use specifically noted in this document, LyondellBasell may further prohibit or restrict the sale of its products into certain applications. For further information, please contact a LyondellBasell representative.

Trademarks

The Trademark referenced within the product name is owned or used by the LyondellBasell family of companies.