

Technical Data Sheet



Polytrope STR 3570EU-01 CLEAR

Enhanced Polyolefin (Capstock Resin)

LyondellBasell Industries

Engineering Plastics

Product Description

POLYTROPE STR 3570EU resin is a high gloss, non-stress whitening, weatherable, olefin cap resin providing exceptional durability. It is specifically designed for the co-extrusion process as a cap resin over ethylene base resins such as HMWPE. It is especially suited for thermoformed applications, as it maintains its clarity, DOI, and high gloss through the thermoforming process. POLYTROPE STR 3570EU-01 CLEAR can be used as a clear cap or it can be easily colored. The high clarity, gloss and durability of the cap resin enables it to provide an economical solution to produce high gloss appearance parts in HMWPE.

General

Material Status	• Commercial: Active		
Availability	• North America		
Features	• Chemical Resistant • Durable • Good Scratch Resistance	• Good Weather Resistance • High Clarity • Low Temperature Impact Resistance	• Recyclable Material • Stain Resistant • Stress Whitening Resistant
Forms	• Pellets		
Processing Method	• Coextrusion • Extrusion	• Profile Extrusion • Sheet Extrusion	• Thermoforming

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density / Specific Gravity ¹	0.930	0.928 g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	0.79 g/10 min	0.79 g/10 min	ISO 1133
Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Stress ² (Yield, 73°F (23°C))	2400 psi	16.5 MPa	ISO 527-2
Tensile Strain ² (Break, 451°F (233°C))	250 %	250 %	ISO 527-2
Flexural Modulus - Chord ³ (73°F (23°C))	55000 psi	379 MPa	ISO 178
Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Instrumented Dart Impact -22°F (-30°C), Total Energy, Ductile Failure	340 in-lb	38.4 J	ASTM D3763
Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Deflection Temperature Under Load 66 psi (0.45 MPa), Unannealed	130 °F	54.4 °C	ISO 75-2/Bf
Flammability	Nominal Value (English)	Nominal Value (SI)	Test Method
Flame Rating (0.13 in (3.2 mm), All Colors)	HB	HB	UL 94
Optical	Nominal Value (English)	Nominal Value (SI)	Test Method
Gloss 60°, 125 mil (3180 µm), Thermoformed, Smooth	50 to 70	50 to 70	ISO 2813

Notes

¹ Method A

² Type 1, 2.0 in/min (50 mm/min)

³ Type 1A, 0.079 in/min (2.0 mm/min)

Notes

These are typical property values not to be construed as specification limits.

Processing Techniques

Specific recommendations for resin type and processing conditions can only be made when the end use, required properties and fabrication equipment are known.

Product Storage and Handling

- Product should be stored in dry conditions at temperatures below 50°C and protected from UV-light
- Improper storage may bring damage to the packaging and can negatively affects on the quality of this product
- Keep material completely dry for good processing

Technical Data Sheet

**Polytrope STR 3570EU-01 CLEAR**

Enhanced Polyolefin (Capstock Resin)
LyondellBasell Industries
Engineering Plastics

Company Information

For further information regarding the LyondellBasell company, please visit <http://www.lyb.com/>.

© LyondellBasell Industries Holdings, B.V. 2024

Disclaimer

Information in this document is accurate to the best of our knowledge at the date of publication. The document is designed to provide users general information for safe handling, use, processing, storage, transportation, disposal and release and does not constitute any warranty or quality specification, either express or implied, including any warranty of merchantability or fitness for any particular purpose. Users shall determine whether the product is suitable for their use and can be used safely and legally.

In addition to any prohibitions of use specifically noted in this document, LyondellBasell may further prohibit or restrict the sale of its products into certain applications. For further information, please contact a LyondellBasell representative.

Trademarks

The Trademark referenced within the product name is owned or used by the LyondellBasell family of companies.