


Petrothene®

GA818073

Linear Low Density Polyethylene
Blow Molding Grade
Melt Index 0.75 Density 0.9205
Applications

PETROTHENE GA 818073 offers the high environmental stress crack resistance characteristics of linear low density polyethylene with the processing properties needed for blowmolding and extrusion applications. The broad molecular weight distribution of GA818073 combines good melt strength with a significantly reduced tendency to melt fracture, two drawbacks common to conventional fractional melt index LLDPE resins. Applications for this resin include beverage and drip irrigation tubing, squeeze tubes and bottles for pharmaceutical and personal care product packaging, drum liners, highway traffic channellizers and other large, blow molded parts.

Regulatory Status

GA818073 meets the specifications of the Food and Drug Administration regulation 21 CFR 177.1520. This regulation allows for the use of this olefin polymer in "...articles or components of articles intended for use in contact with food." Specific limitations or conditions of use may apply. Contact your Equistar sales representative for more information.

Processing Techniques

Processing conditions can only be recommended when the type of equipment and the end-use application are known. For further suggestions, please contact your Equistar sales representative.

Typical Properties

Property	Nominal Value	Units	ASTM Test Method
Melt Index	0.75	g/10 min	D 1238
Density	0.9205	g/cc	D 1505
Tensile Strength @ Break	2,170	psi	D 638*
Elongation @ Break	>700	%	D 638*
Flexural Modulus	40,000	psi	D 790
Low Temperature Brittleness, F ₅₀	<-42	°C	D 746**
Heat Deflection Temperature @66 psi	48	°C	D 648
Vicat Softening Point	88	°C	D 1525
Hardness, Shore D	51		D 2240
Environmental Stress Crack Resistance, F ₅₀	>1,000	hrs	D 2561

* Type IV specimen

** Injection molded specimen

The information on this document is, to our knowledge, true and accurate. However, since the particular uses and the actual conditions of use of our products are beyond our control, establishing satisfactory performance of our products for the intended application is the customer's sole responsibility. All uses of Equistar products and any written or oral information, suggestions or technical advice from Equistar are without warranty, express or implied, and are not an inducement to use any process or product in conflict with any patent.

Equistar materials are not designed or manufactured for use in implantation in the human body or in contact with internal body fluids or tissues. Equistar makes no representation, promise, express warranty or implied warranty concerning the suitability of these materials for use in implantation in the human body or in contact with internal body tissues or fluids.

More detailed safety and disposal information on our products is contained in the Material Safety Data Sheet (MSDS). All users of our products are urged to retain and use the MSDS. A MSDS is automatically distributed upon purchase/order execution. You may request an advance or replacement copy by calling our MSDS Hotline at 800.700.0946.

® Petrothene is a registered trademark of Equistar Chemicals, LP.



Lyondell Chemical Company
 1221 McKinney, Suite 700
 P.O. Box 2583
 Houston, Texas 77252-2583
 800.615.8999
<http://www.lyondell.com>